

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
13 November 2003 (13.11.2003)

PCT

(10) International Publication Number
WO 03/092745 A1

(51) International Patent Classification⁷: **A61L 2/08**,
2/10, A01N 1/02

[CA/US]; 9971 Lake Landing Road, Montgomery Village,
MD 20886 (US).

(21) International Application Number: **PCT/US03/12827**

(74) Agents: **FLESHNER, Mark L. et al.**; FLESHNER &
KIM, LLP, P.O. Box 221200, Chantilly, VA 20153-1200
(US).

(22) International Filing Date: **24 April 2003 (24.04.2003)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
10/133,631 **29 April 2002 (29.04.2002)** **US**

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (*for all designated States except US*): **CLEAR-
ANT, INC.** [US/US]; 11111 Santa Monica Boulevard,
Suite 650, Los Angeles, CA 90025 (US).

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **GREIB, Teri**
[US/US]; 26800 Grace Court, Damascus, MD 20872
(US). **MANN, David M.** [US/US]; 7430 Brenish Drive,
Gaithersburg, MD 20879 (US). **STAFFORD, Richard**
E. [US/US]; 1001 Wilson Boulevard, Apartment 705,
Arlington, VA 22209 (US). **BURGESS, Wilson H.**
[US/US]; 12824 Great Oak Lane, Clifton, VA 20124 (US).
DROHAN, William N. [US/US]; 8417 Oakford Lane,
Springfield, VA 22152 (US). **MACPHEE, Martin J.**

Published:

— *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 03/092745 A1

(54) Title: **METHODS FOR STERILIZING TISSUES USING CRYOPRESERVATIVES**

(57) Abstract: Methods are disclosed for sterilizing tissue to reduce the level of one or more active biological contaminants or pathogens therein, such as viruses, bacteria, (including inter- and intracellular bacteria, such as mycoplasmas, ureaplasmas, nanobacteria, chlamydia, rickettsias), yeasts, molds, fungi, spores, prions or similar agents responsible, alone or in combination, for TSEs and/or single or multicellular parasites. The methods involve sterilizing one or more tissues with irradiation.

METHODS FOR STERILIZING TISSUE USING CRYOPRESERVATIVES

BACKGROUND OF THE INVENTION

Field of the Invention

5 The present invention relates to methods for sterilizing tissue to reduce the level of one or more active biological contaminants or pathogens therein, such as viruses, bacteria (including inter- and intracellular bacteria, such as mycoplasmas, ureaplasmas, nanobacteria, chlamydia, rickettsias), yeasts, molds, fungi, spores, prions or similar agents responsible, alone or in combination, for transmissible spongiform encephalopathies (TSEs) and/or single or multicellular
10 parasites. The present invention particularly relates to methods of sterilizing tissue with irradiation, wherein the tissue may subsequently be used in transplantation to replace diseased and/or otherwise defective tissue in an animal.

Background of the Related Art

15 Many biological materials that are prepared for human, veterinary, diagnostic and/or experimental use may contain unwanted and potentially dangerous biological contaminants or pathogens, such as viruses, bacteria, in both vegetative and spore states, (including inter- and intracellular bacteria, such as mycoplasmas, ureaplasmas, nanobacteria, chlamydia, rickettsias), yeasts, molds, fungi, prions or similar agents responsible, alone or in combination, for TSEs and/or single-cell or multicellular parasites. Consequently, it is of utmost importance that any biological
20 contaminant or pathogen in the biological material be inactivated before the product is used. This is especially critical when the material is to be administered directly to a patient, for example in blood transfusions, blood factor replacement therapy, tissue implants, including organ transplants, and other forms of human and/or other animal therapy corrected or treated by surgical implantation, intravenous, intramuscular or other forms of injection or introduction. This is also critical for the
25 various biological materials that are prepared in media or via the culture of cells, or recombinant cells which contain various types of plasma and/or plasma derivatives or other biologic materials and which may be subject to mycoplasmal, prion, ureaplasma, bacterial, viral and/or other biological contaminants or pathogens.

30 Recently, the safety of the widespread practice in orthopedic medicine of using human donor tissue to replace damaged cartilage or tendons has come into question. In fact, Federal investigators started looking into the deaths of three patients in Minnesota following knee surgery and found that some people have contracted severe infections after receiving implanted knee

tissue, which appeared to be infected with a type of bacteria, known as *Clostridium*. Maura Lerner, et al, "Knee Surgery Deaths Turn Focus on Donor Tissue", Star Tribune, Dec. 8, 2001. See also "Septic Arthritis Following Anterior Cruciate Ligament Reconstruction Using Tendon Allografts — Florida and Louisiana, 2000", MMWR Weekly, 50(48):1081-1083 (December 7, 2001).

5 The tissue in these knee surgery cases was cartilage, which is not sterilized as it is believed such sterilization would damage the implant. Instead, tissue suppliers attempt to provide safe tissue through screening donors, testing for bacteria and applying antibiotic solutions. In fact, many procedures for producing human compatible biological materials have involved methods that screen or test the biological materials for one or more particular biological contaminants or
10 pathogens rather than removal or inactivation of the contaminant(s) or pathogen(s) from the biological material. The typical protocol for disposition of materials that test positive for a biological contaminant or pathogen simply is non-use/discarding of that material. In certain cases, known microbial contaminants may be permitted in the implant material at the time it is harvested from the host organism. Examples of screening procedures for contaminants include testing for a particular
15 virus in human blood and tissues from donors. Such procedures, however, are not always reliable, as evidenced by the death of at least one Minnesota man who received a cartilage implant, and are not able to detect the presence of prions or certain viruses, particularly those present in very low numbers. This reduces the value, certainty, and safety of such tests in view of the consequences associated with a false negative result, which can be life threatening in certain cases, for example
20 in the case of Acquired Immune Deficiency Syndrome (AIDS). Furthermore, in some instances it can take weeks, if not months, to determine whether or not the material is contaminated. Moreover, to date, there is no commercially available, reliable test or assay for identifying prions, ureaplasmas, mycoplasmas, and chlamydia within a biological material that is fully suitable for screening out potential donors or infected material (*Advances in Contraception* 10(4):309-
25 315(1994)). This serves to heighten the need for an effective means of destroying prions, ureaplasmas, mycoplasmas, chlamydia, etc., within a biological material, while still retaining the desired activity of that material. Therefore, it would be desirable to apply techniques that would kill or inactivate contaminants or pathogens during and/or after manufacturing and/or harvesting the biological material.

30 The importance of ready availability of effective techniques is apparent regardless of the source of the biological material. All living cells and multi-cellular organisms can be infected with viruses and other pathogens. Thus, the products of unicellular natural or recombinant organisms or tissues virtually always carry a risk of pathogen contamination. In addition to the risk that the

producing cells or cell cultures may be infected, the processing of these and other biological materials also creates opportunities for environmental contamination. The risks of infection are more apparent for multicellular natural and recombinant organisms, such as transgenic animals. Interestingly, even products from species as different from humans as transgenic plants carry risks, both due to processing contamination as described above, and from environmental contamination in the growing facilities, which may be contaminated by pathogens from the environment or infected organisms that co-inhabit the facility along with the desired plants. For example, a crop of transgenic corn grown out doors, could be expected to be exposed to rodents such as mice during the growing season. Mice can harbor serious human pathogens such as the frequently fatal Hanta virus. Since these animals would be undetectable in the growing crop, viruses shed by the animals could be carried into the transgenic material at harvest. Indeed, such rodents are notoriously difficult to control, and may gain access to a crop during sowing, growth, harvest or storage. Likewise, contamination from overflying or perching birds has the potential to transmit such serious pathogens as the causative agent for psittacosis. Thus, any biological material, regardless of its source, may harbor serious pathogens that must be removed or inactivated prior to administration of the material to a recipient human or other animal.

In conducting experiments to determine the ability of technologies to inactivate viruses, the actual viruses of concern are seldom utilized. This is a result of safety concerns for the workers conducting the tests, and the difficulty and expense associated with facilities for containment and waste disposal. In their place, model viruses of the same family and class are usually used. In general, it is acknowledged that the most difficult viruses to inactivate are those with an outer shell made up of proteins, and that among these, the most difficult to inactivate are those of the smallest size. This has been shown to be true for gamma irradiation and most other forms of radiation because these viruses= diminutive size is associated with a small genome. The magnitude of direct effects of radiation upon a molecule is directly proportional to the size of the molecule; that is, the larger the target molecule, the greater is the effect. As a corollary, it has been shown for gamma-irradiation that the smaller the viral genome, the higher is the radiation dose required to inactivate it

Among the viruses of concern for both human and animal-derived biological materials, the smallest, and thus most difficult to inactivate, belong to the family of Parvoviruses and the slightly larger protein-coated Hepatitis virus. In humans, the Parvovirus B19, and Hepatitis A are the agents of concern. In porcine-derived materials, the smallest corresponding virus is Porcine Parvovirus. Since this virus is harmless to humans, it is frequently chosen as a model virus for the

human B19 Parvovirus. The demonstration of inactivation of this model parvovirus is considered adequate proof that the method employed will kill human B19 virus and Hepatitis A, and, by extension, that it will also kill the larger and less hardy viruses, such as HIV, CMV, Hepatitis B, Hepatitis C, and others.

5 More recent efforts have focused on methods to remove or inactivate contaminants in products intended for use in humans and other animals. Such methods include heat treating, filtration and the addition of chemical inactivants or sensitizers to the product.

According to current standards of the U.S. Food and Drug Administration, heat treatment of biological materials may require heating to approximately 60°C for a minimum of 10 hours, which
10 can be damaging to sensitive biological materials. Indeed, heat inactivation can destroy 50% or more of the biological activity of certain biological materials. Tissues are particularly sensitive to these high temperature treatments.

Filtration involves filtering the product in order to physically remove contaminants. Unfortunately, this method may also remove products that have a high molecular weight. Further,
15 in certain cases, small viruses may not be removed by the filter.

The procedure of chemical sensitization involves the addition of noxious agents which bind to the DNA/RNA of the virus, and which are activated either by UV or other radiation. This radiation produces reactive intermediates and/or free radicals which bind to the DNA/RNA of the virus, break the chemical bonds in the backbone of the DNA/RNA, and/or cross-link or complex it in such a way
20 that the virus can no longer replicate. This procedure requires that unbound sensitizer be washed from products since the sensitizers are toxic, if not mutagenic or carcinogenic, and cannot be administered to a patient.

Irradiating a product with gamma radiation is another method of sterilizing a product. Gamma radiation is effective in destroying viruses and bacteria when given in high total doses.
25 (Keathly, *et al.*, "Is There Life After Irradiation? Part 2," *BioPharm* July-August, 1993, and Leitman, "Use of Blood Cell Irradiation in the Prevention of Post Transfusion Graft-vs-Host Disease," *Transfusion Science* 10:219-239(1989)). The published literature in this area, however, teaches that gamma radiation can be damaging to radiation sensitive products, such as blood, blood products, tissues, protein and protein-containing products. In particular, it has been shown that
30 high radiation doses are injurious to red blood cells, platelets and granulocytes (Leitman). U.S. Patent No. 4,620,908 discloses that protein products must be frozen prior to irradiation in order to maintain the viability of the protein product. This patent concludes that "if the gamma irradiation

were applied while the protein material was at, for example, ambient temperature, the material would be also completely destroyed, that is the activity of the material would be rendered so low as to be virtually ineffective." Unfortunately, many sensitive biological materials, such as monoclonal antibodies (Mab), may lose viability and activity if subjected to freezing for irradiation purposes and then thawing prior to administration to a patient.

It has recently been reported that federal officials had turned up at least 25 cases of serious bacterial infections in people who received tissue transplants; at least one case resulted in death. (The New York Times, March 15, 2002). In the case resulting in death, the Centers for Disease Control and Prevention in Atlanta found that the tissue that had fatally infected a Minnesotan who was having kneecap repair surgery had not been refrigerated until 19 hours after the donor's death, by which time lethal bacteria from the donor's intestines might have spilled into his body. As noted in the article, gamma irradiation may be used to kill various pathogens. However, according to a representative of the CDC, such irradiation may result in weakened tissue, like cartilage and tendons, used to repair damaged joints. Therefore, there is a recognition in the art of a long felt need for improved methods of sterilizing tissue without deleteriously affecting the tissue. See also, U.S. Patent Nos. 6,326,018 and 6,203,755.

When the product to be sterilized is biological tissue that is to be transplanted, even greater sensitivity to irradiation or other sterilization methods is often encountered. This greater sensitivity is the result of the molecular integration of the biochemical, physiological, and anatomical systems that is required for normal function of that biological tissue. Thus, special procedures are typically required to maintain the tight molecular integration that underpins normal function during and after transplantation of a biological tissue. Furthermore, special procedures may be required in addition to other considerations, such as histocompatibility (matching of HLA types, etc.) between donor and recipient, and including compatibility between species when there is inter-species (i.e., heterografting) transplantation.

Tissues and organs that may be used in transplantation are numerous. Non-limiting examples include heart, lung, liver, spleen, pancreas, kidney, corneas, bone, joints, bone marrow, blood cells (red blood cells, leucocytes, lymphocytes, platelets, etc.), plasma, skin, fat, tendons, ligaments, hair, muscles, blood vessels (arteries, veins), teeth, gum tissue, fetuses, eggs (fertilized and not fertilized), eye lenses, and even hands. Active research may soon expand this list to permit transplantation of nerve cells, nerves, and other physiologically and anatomically complex tissues, including intestine, cartilage, entire limbs, and portions of brain.

As surgical techniques become more sophisticated, and as storage and preparation techniques improve, the demand for various kinds of transplantation may reasonably be expected to increase over current levels.

Another factor that may feed future transplantation demand is certain poor lifestyle choices in the population, including such factors as poor nutrition (including such trends as the increasing reliance on so-called fast foods and fried foods; insufficient intake of fruits, vegetables and true whole grains; and increased intake of high glycemic, low nutritional value foods, including pastas, breads, white rice, crackers, potato chips and other snack foods, etc.), predilections toward a sedentary lifestyle, and over-exposure to ultraviolet light in tanning booths and to sunlight. The increasing occurrence of such factors as these have resulted, for example, in increased incidences of obesity (which also exacerbates such conditions as arthritis and conditions with cartilage damage, as well as impairs wound healing, immune function, cancer risk, etc.), type II diabetes and polycystic ovary syndrome (high post prandial glucose values causing damage to such tissues as nerve, muscle, kidney, heart, liver, etc., causing tissue and organ damage even in persons who are not diabetic), many cancers, and hypertension and other cardiovascular conditions, such as strokes and Alzheimer=s disease (recent data suggesting that Alzheimer=s may be the result of a series of mini-strokes). Thus, poor lifestyle choices ultimately will increase demand for bone, cartilage, skin, blood vessels, nerves, and the specific tissues and organs so destroyed or damaged.

Infections comprise yet another factor in transplantation demand. Not only can bacterial and viral infections broadly damage the infected host tissue or organ, but they can also spread vascularly or by lymphatics to cause lymph vessel or vascular inflammation, and/or plaque build up that ultimately results in infarct (for example, stroke, heart attack, damaged or dead tissue in lung or other organ, etc.). In addition, there is an epidemic of infection by intracellular microbes for which reliable commercial tests are not available (for example, mycoplasma, ureaplasma, and chlamydia), for example, as a result of sexual contact, coughing, etc. [for example, more than 20% of sore throats in children are due to chlamydia (E. Normann, *et al.*, "Chlamydia Pneumoniae in Children Undergoing Adenoidectomy," *Acta Paediatrica* 90(2):126-129(2001))].

Some intravascular infectious agents, via the antibodies that are produced to fight them, result in attack of tissue having surface molecules that have a molecular structure similar to the structure of surface or other groups of the infectious agent. Such is the case with some *Streptococci* infections (antibodies produced against M proteins of *Streptococci* that cross-react with cardiac, joint and other tissues), for example, in which tissue and other cardiac tissue may be attacked to cause reduced cardiac function, and which can result in death if the infection is not

properly treated before extensive damage occurs. Another antibody mediated condition that can affect cardiac tissue, among other tissues/cells, is antiphospholipid antibody syndrome (APLA), in which antibodies are directed against certain phospholipids (cardiolipin) to produce a hypercoagulable state, thrombocytopenia, fetal loss, dementia, strokes, optic changes, Addison's disease, and skin rashes, among other symptoms. Tissue vegetations and mitral regurgitation are common in intravascular infections, although tissue destruction so extensive as to require valve replacement is rare.

Other intravascular infectious agents directly attack tissues and organs in/on which they establish colonies. Non-limiting examples include *Staphylococci* (including, for example, *S. aureus*, *S. epidermidis*, *S. saprophyticus*, among others), *Chlamydia* (including, for example, *C. pneumoniae*, among others), *Streptococci* (including, for example, the viridians group of *Streptococci*: *S. sanguis*, *S. oralis* (mitis), *S. salivarius*, *S. mutans*, and others; and other species of *Streptococci*, such as *S. bovis* and *S. pyogenes*), *Enterococci* (for example, *E. faecalis* and *E. faecium*, among others), various fungi, and the AHACEK@ group of gram-negative bacilli (*Haemophilus parainfluenzae*, *Haemophilus aphrophilus*, *Actinobacillus actinomycetemcomitans*, *Cardiobacterium hominis*, *Eikenella corrodens*, and *Kingella kingae*), *Neisseria gonorrhoeae*, *Clostridia* sp., *Listeria monocytogenes*, *Salmonella* sp., *Bacteroides fragilis*, *Escherichia coli*, *Proteus* sp., mycoplasmas, ureaplasmas, various viruses (for example, cytomegalovirus, HIV, and herpes simplex virus), and *Klebsiella-Enterobacter-Serratia* sp., among others.

An exemplary study by Nystrom-Rosander, et al. may be cited for showing the presence of *Chlamydia pneumoniae* in sclerotic tissue that required replacement as a result of the sclerosis. (C. Nystrom-Rosander, et al., A High Incidence of *Chlamydia pneumoniae* in Sclerotic Tissue of Patients Undergoing Aortic Valve Replacement, @ *Scandinavian Journal of Infectious Disease* 29:361-365 (1997)).

Yet another factor in transplantation demand is drug use, particularly the use of illicit drugs, but also including inappropriate and sometimes illegal use of otherwise licit drugs (such as overuse of alcohol/alcoholism causing cirrhosis of the liver, and therefore requiring liver transplantation). Such drug use often strongly damages or even destroys sensitive tissues and organs such as kidney, liver, lung, heart, brain/nerves, and/or portions thereof. In addition, intravenous drug use greatly increases the odds of contracting intravascular infections by any one or more of the above-cited infectious agents (among many others), which infections can attack virtually any organ or portion thereof, including the tricuspid valve (located between the right atrium and the right ventricle), the mitral valve (located between the left atrium and the left ventricle), the pulmonary or

pulmonic valve (located between the right ventricle and the pulmonary artery), and the aortic valve (located between the left ventricle and the aorta) with any infectious agent that may enter through implanted tissue.

5 In view of the difficulties discussed above, there remains a need for methods of sterilizing biological materials that are effective for reducing the level of active biological contaminants or pathogens without an adverse effect on the material(s).

The above references are incorporated by reference herein where appropriate for appropriate teachings of additional or alternative details, features and/or technical background.

SUMMARY OF THE INVENTION

10 An object of the invention is to solve at least the related art problems and disadvantages, and to provide at least the advantages described hereinafter.

Accordingly, it is an object of the present invention to provide methods of sterilizing tissue by reducing the level of active biological contaminants or pathogens without adversely affecting the tissue or other material. Other objects, features and advantages of the present invention will be set
15 forth in the detailed description of preferred embodiments that follows, and in part will be apparent from the description or may be learned by practice of the invention. These objects and advantages of the invention will be realized and attained by the compositions and methods particularly pointed out in the written description and claims hereof.

In accordance with these and other objects, a first embodiment of the present invention is
20 directed a method for sterilizing one or more tissues that are sensitive to radiation, the method comprising: (i) adding to the one or more tissues at least one stabilizer; and (ii) irradiating the one or more tissues with radiation for a time effective to sterilize the one or more tissues and at a rate effective to sterilize the one or more tissues, wherein the at least one stabilizer and the rate of irradiation are together effective to protect the one or more tissues from the radiation.

25 Another embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to the one or more tissues at least one cryopreservative; and (ii) irradiating the one or more tissues with radiation for a time effective to sterilize the one or more tissues and at a rate effective to sterilize the one or more tissues.

30 Another embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to the one or more

tissues at least one stabilizer; (ii) subjecting the at least one tissue to a treatment effective to enhance penetration of the at least one stabilizer into the one or more tissues; and (iii) irradiating the one or more tissues with radiation for a time effective to sterilize the one or more tissues and at a rate effective to sterilize the one or more tissues wherein said at least one stabilizer and the rate of irradiation are together effective to protect said one or more tissue from said radiation.

Another embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to the one or more tissues at least one cryopreservative; (ii) subjecting the one or more tissues to a treatment effective to enhance penetration of the at least one cryopreservative into the one or more tissues; and (iii) irradiating the one or more tissues with radiation for a time effective to sterilize the one or more tissues and at a rate effective to sterilize the one or more tissues.

Another embodiment of the present invention is directed to a composition including one or more tissues and at least one cryopreservative in an amount effective to preserve the one or more tissues for their intended use following sterilization with radiation.

Additional advantages, objects, and features of the invention will be set forth in part in the description which follows and in part will become apparent to those having ordinary skill in the art upon examination of the following or may be learned from practice of the invention. The objects and advantages of the invention may be realized and attained as particularly pointed out in the appended claims.

BRIEF DESCRIPTION OF THE DRAWINGS

Figures 1A-1D show the effects of gamma irradiation on porcine heart valves in the presence of polypropylene glycol 400 and, optionally, a scavenger.

Figures 2A-2E show the effects of gamma irradiation on porcine heart valve cusps in the presence of 50% DMSO and, optionally, a stabilizer, and in the presence of polypropylene glycol 400.

Figures 3A-3E show the effects of gamma irradiation on frozen porcine AV heart valves soaked in various solvents and irradiated to a total dose of 30kGy at 1.584kGy/hr at -20°C.

Figures 4A-4H show the effects of gamma irradiation on frozen porcine AV heart valves soaked in various solvent and irradiated to a total dose of 45kGy at approximately 6kGy/hr at -70°C.

Figures 5A-5E show the effects of gamma irradiation on frozen porcine ACL tissue soaked in a stabilizer cocktail and irradiated to a total dose of 45kGy at approximately 6kGy/hr at -80°C.

Figures 6A-6F show the effects of gamma irradiation on frozen porcine ACL tissue soaked in the various stabilizers.

5 Figures 7A-7C show the effects of gamma irradiation on frozen porcine ACL tissue soaked in cryopreservatives using either regulated freeze or quick freeze.

Figure 8 shows the effects of a combination of ethanol dehydration or drying to remove water and rehydration to deliver a stabilizer cocktail to frozen porcine ACL tissue to protect the samples from gamma irradiation to a total dose of 50kGy at 4°C.

10 Figures 9A-9B show the effects of salts and pH levels on scavengers inside ACL tissue to protect the ACL tissue from gamma irradiation to a total dose of 50kGy at -80°C.

Figure 10 shows the effects of gamma irradiation on frozen porcine ACL tissue soaked in various alcohols and irradiated to a total dose of 50kGy at -80°C.

15 Figure 11 shows the effects of gamma irradiation on fresh frozen, freeze-dried or solvent dried porcine ACL tissue irradiated to a total dose of 45kGy at about -72°C.

Figures 12A-12C show the effects of gamma irradiation on type I collagen treated with various stabilizers and irradiated to a total dose of 45kGy at -20°C, -80°C or freeze dried at 4°C.

Figure 13 shows the effects of gamma irradiation on liquid and gel collagen treated with various stabilizers.

20 Figures 14A-14D show the effects of gamma irradiation on collagen treated with various stabilizers.

Figure 15 shows the effects of gamma irradiation on porcine ACL treated with various stabilizers.

25 Figures 16-20 show the effects of gamma irradiation on porcine heart valves treated with various freezing methods in the presence or absence of various cryopreservatives.

Figures 21-23 show the effects of gamma irradiation on porcine heart valves treated with various freezing methods in the presence or absence of various cryopreservatives.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS**A. Definitions**

Unless defined otherwise, all technical and scientific terms used herein are intended to have the same meaning as is commonly understood by one of ordinary skill in the relevant art.

- 5 As used herein, the singular forms "a," "an," and "the" include the plural reference unless the context clearly dictates otherwise.

As used herein, the term "sterilize" is intended to mean a reduction in the level of at least one active biological contaminant or pathogen found in the tissue being treated according to the present invention.

- 10 As used herein, the term "non-aqueous solvent" is intended to mean any liquid other than water in which a biological material, such as one or more tissues, may be dissolved or suspended or which may be disposed within a biological material, such as one or more tissues, and includes both inorganic solvents and, more preferably, organic solvents. Illustrative examples of suitable non-aqueous solvents include, but are not limited to, the following: alkanes and cycloalkanes, such as pentane, 2-methylbutane (isopentane), heptane, hexane, cyclopentane and cyclohexane; 15 alcohols, such as methanol, ethanol, 2-methoxyethanol, isopropanol, n-butanol, t-butyl alcohol, and octanol; esters, such as ethyl acetate, 2-methoxyethyl acetate, butyl acetate and benzyl benzoate; aromatics, such as benzene, toluene, pyridine, xylene; ethers, such as diethyl ether, 2-ethoxyethyl ether, ethylene glycol dimethyl ether and methyl t-butyl ether; aldehydes, such as formaldehyde and glutaraldehyde; ketones, such as acetone and 3-pentanone (diethyl ketone); glycols, including 20 both monomeric glycols, such as ethylene glycol and propylene glycol, and polymeric glycols, such as polyethylene glycol (PEG) and polypropylene glycol (PPG), e.g., PPG 400, PPG 1200 and PPG 2000; acids and acid anhydrides, such as formic acid, acetic acid, trifluoroacetic acid, phosphoric acid and acetic anhydride; oils, such as cottonseed oil, peanut oil, culture media, polyethylene glycol, poppyseed oil, safflower oil, sesame oil, soybean oil and vegetable oil; amines and amides, 25 such as piperidine, N,N-dimethylacetamide and N,N-dimethylformamide; dimethylsulfoxide (DMSO); nitriles, such as benzonitrile and acetonitrile; hydrazine; detergents, such as polyoxyethylenesorbitan monolaurate (Tween 20) and monooleate (Tween 80), Triton and sodium dodecyl sulfate; carbon disulfide; halogenated solvents, such as dichloromethane, chloroform, carbon tetrachloride, 1,2-dichlorobenzene, 1,2-dichloroethane, tetrachloroethylene and 1-chlorobutane; furans, such as tetrahydrofuran; oxanes, such as 1,4-dioxane; and glycerin/glycerol. 30

Particularly preferred examples of suitable non-aqueous solvents include non-aqueous solvents which also function as stabilizers, such as ethanol and acetone.

As used herein, the term "biological contaminant or pathogen" is intended to mean a biological contaminant or pathogen that, upon direct or indirect contact with a biological material, such as one or more tissues, may have a deleterious effect on the biological material or upon a recipient thereof. Such other biological contaminants or pathogens include the various viruses, bacteria, in both vegetative and spore states, (including inter- and intracellular bacteria, such as mycoplasmas, ureaplasmas, nanobacteria, chlamydia, rickettsias), yeasts, molds, fungi, prions or similar agents responsible, alone or in combination, for TSEs and/or single or multicellular parasites known to those of skill in the art to generally be found in or infect biological materials. Examples of other biological contaminants or pathogens include, but are not limited to, the following: viruses, such as human immunodeficiency viruses and other retroviruses, herpes viruses, filoviruses, circoviruses, paramyxoviruses, cytomegaloviruses, hepatitis viruses (including hepatitis A, B, C, and D variants thereof, among others), pox viruses, toga viruses, Epstein-Barr viruses and parvoviruses; bacteria, such as *Escherichia*, *Bacillus*, *Campylobacter*, *Streptococcus* and *Staphylococcus*; nanobacteria; parasites, such as *Trypanosoma* and malarial parasites, including *Plasmodium* species; yeasts; molds; fungi; mycoplasmas and ureaplasmas; chlamydia; rickettsias, such as *Coxiella burnetii*; and prions and similar agents responsible, alone or in combination, for one or more of the disease states known as transmissible spongiform encephalopathies (TSEs) in mammals, such as scrapie, transmissible mink encephalopathy, chronic wasting disease (generally observed in mule deer and elk), feline spongiform encephalopathy, bovine spongiform encephalopathy (mad cow disease), Creutzfeld-Jakob disease (including variant CJD), Fatal Familial Insomnia, Gerstmann-Straeussler-Scheinker syndrome, kuru and Alpers syndrome. As used herein, the term "active biological contaminant or pathogen" is intended to mean a biological contaminant or pathogen that is capable of causing a deleterious effect, either alone or in combination with another factor, such as a second biological contaminant or pathogen or a native protein (wild-type or mutant) or antibody, in a biological material, such as one or more tissues, and/or a recipient thereof.

As used herein, the term "a biologically compatible solution" is intended to mean a solution to which a biological material, such as one or more tissues, may be exposed, such as by being suspended or dissolved therein, and retain its essential biological and physiological characteristics. Such solutions may be of any suitable pH, tonicity, concentration and/or ionic strength.

As used herein, the term "a biologically compatible buffered solution" is intended to mean a biologically compatible solution having a pH and osmotic properties (e.g., tonicity, osmolality and/or oncotic pressure) suitable for maintaining the integrity of the material(s) therein, such as one or more tissues. Suitable biologically compatible buffered solutions typically have a pH between 2 and 8.5 and are isotonic or only moderately hypotonic or hypertonic. Biologically compatible buffered solutions are known and readily available to those of skill in the art. Greater or lesser pH and/or tonicity may also be used in certain applications. The ionic strength of the solution may be high or low, but is typically similar to the environments in which the tissue is intended to be used.

As used herein, the term "stabilizer" is intended to mean a compound or material that, alone and/or in combination, reduces damage to one or more tissues being irradiated to a level that is insufficient to preclude the safe and effective use of the material. Illustrative examples of stabilizers that are suitable for use include, but are not limited to, the following, including structural analogs and derivatives thereof: antioxidants; free radical scavengers, including spin traps, such as tert-butyl-nitrosobutane (tNB), α -phenyl-tert-butyl nitron (PBN), 5,5-dimethylpyrroline-N-oxide (DMPO), tert-butyl nitrosobenzene (BNB), α -(4-pyridyl-1-oxide)-N-tert-butyl nitron (4-POBN) and 3,5-dibromo-4-nitroso-benzenesulphonic acid (DBNBS); combination stabilizers, i.e., stabilizers which are effective at quenching both Type I and Type II photodynamic reactions; and ligands, ligand analogs, substrates, substrate analogs, modulators, modulator analogs, stereoisomers, inhibitors, and inhibitor analogs, such as heparin, that stabilize the molecule(s) to which they bind. Preferred examples of additional stabilizers include, but are not limited to, the following: fatty acids, including 6,8-dimercapto-octanoic acid (lipoic acid) and its derivatives and analogues (α , β , dihydro, bisno and tetranor lipoic acid), thiocctic acid, 6,8-dimercapto-octanoic acid, dihydrolopoate (DL-6,8-dithioloctanoic acid methyl ester), lipoamide, bisonor methyl ester and tetranor-dihydrolipoic acid, omega-3 fatty acids, omega-6 fatty acids, omega-9 fatty acids, furan fatty acids, oleic, linoleic, linolenic, arachidonic, eicosapentaenoic (EPA), docosahexaenoic (DHA), and palmitic acids and their salts and derivatives; carotenes, including α -, β -, and gamma-carotenes; Co-Q10; xanthophylls; sucrose, polyhydric alcohols, such as glycerol, mannitol, inositol, and sorbitol; sugars, including derivatives and stereoisomers thereof, such as xylose, glucose, ribose, mannose, fructose, erythrose, threose, idose, arabinose, lyxose, galactose, allose, altrose, gulose, talose, and trehalose; amino acids and derivatives thereof, including both D- and L-forms and mixtures thereof, such as arginine, lysine, alanine, valine, leucine, isoleucine, proline, phenylalanine, glycine, serine, threonine, tyrosine, asparagine, glutamine, aspartic acid, histidine, N-acetylcysteine (NAC), glutamic acid, tryptophan, sodium capryl N-acetyl-tryptophan, and

methionine; azides, such as sodium azide; enzymes, such as Superoxide Dismutase (SOD), Catalase, and $\Delta 4$, $\Delta 5$ and $\Delta 6$ desaturases; uric acid and its derivatives, such as 1,3-dimethyluric acid and dimethylthiourea; allopurinol; thiols, such as glutathione and reduced glutathione and cysteine; trace elements, such as selenium, chromium, and boron; vitamins, including their

5 precursors and derivatives, such as vitamin A, vitamin C (including its derivatives and salts such as sodium ascorbate and palmitoyl ascorbic acid) and vitamin E (and its derivatives and salts such as alpha-, beta-, gamma-, delta-, epsilon-, zeta-, and eta-tocopherols, tocopherol acetate and alpha-tocotrienol); chromanol-alpha-C6; 6-hydroxy-2,5,7,8-tetramethylchroma-2 carboxylic acid (Trolox) and derivatives; extraneous proteins, such as gelatin and albumin; tris-3-methyl-1-phenyl-2-

10 pyrazolin-5-one (MCI-186); citiolone; puerctin; chrysin; dimethyl sulfoxide (DMSO); piperazine diethanesulfonic acid (PIPES); imidazole; methoxypsoralen (MOPS); 1,2-dithiane-4,5-diol; reducing substances, such as butylated hydroxyanisole (BHA) and butylated hydroxytoluene (BHT); cholesterol, including derivatives and its various oxidized and reduced forms thereof, such as low density lipoprotein (LDL), high density lipoprotein (HDL), and very low density lipoprotein (VLDL);

15 probucol; indole derivatives; thimerosal; lazaroid and tirilazad mesylate; proanthoenols; proanthocyanidins; ammonium sulfate; Pegorgotein (PEG-SOD); N-tert-butyl-alpha-phenylnitron (PBN); 4-hydroxy-2,2,6,6-tetramethylpiperidin-1-oxyl (Tempol); mixtures of ascorbate, urate and Trolox C (Asc/urate/Trolox C); proteins, such as albumin, and peptides of two or more amino acids, any of which may be either naturally occurring amino acids, i.e., L-amino acids, or non-naturally

20 occurring amino acids, i.e., D-amino acids, and mixtures, derivatives, and analogs thereof, including, but not limited to, arginine, lysine, alanine, valine, leucine, isoleucine, proline, phenylalanine, glycine, histidine, glutamic acid, tryptophan (Trp), serine, threonine, tyrosine, asparagine, glutamine, aspartic acid, cysteine, methionine, and derivatives thereof, such as N-acetylcysteine (NAC) and sodium capryl N-acetyl tryptophan, as well as homologous dipeptide

25 stabilizers (composed of two identical amino acids), including such naturally occurring amino acids, as Gly-Gly (glycylglycine) and Trp-Trp, and heterologous dipeptide stabilizers (composed of different amino acids), such as carnosine (β -alanyl-histidine), anserine (β -alanyl-methylhistidine), and Gly-Trp; and flavonoids/flavonols, such as diosmin, quercetin, rutin, silybin, silidianin, silicristin, silymarin, apigenin, apiin, chrysin, morin, isoflavone, flavoxate, gossypetin, myricetin, biacalein,

30 kaempferol, curcumin, proanthocyanidin B2-3-O-gallate, epicatechin gallate, epigallocatechin gallate, epigallocatechin, gallic acid, epicatechin, dihydroquercetin, quercetin chalcone, 4,4'-dihydroxy-chalcone, isoliquiritigenin, phloretin, coumestrol, 4',7-dihydroxy-flavanone, 4',5-dihydroxy-flavone, 4',6-dihydroxy-flavone, luteolin, galangin, equol, biochanin-A, daidzein,

formononetin, genistein, amentoflavone, bilobetin, taxifolin, delphinidin, malvidin, petunidin, pelargonidin, malonylapiin, pinosylvic, 3-methoxyapigenin, leucodelphinidin, dihydrokaempferol, apigenin 7-O-glucoside, pycnogenol, aminoflavone, purpurogallin fisetin, 2',3'-dihydroxyflavone, 3-hydroxyflavone, 3',4'-dihydroxyflavone, catechin, 7-flavonoxycetic acid ethyl ester, catechin, hesperidin, and naringin. Particularly preferred examples include single stabilizers or combinations of stabilizers that are effective at quenching both Type I and Type II photodynamic reactions, and volatile stabilizers, which can be applied as a gas and/or easily removed by evaporation, low pressure, and similar methods. Additional preferred examples for use in the methods of the present invention include hydrophobic stabilizers. Stabilizers may also act as cryopreservatives.

As used herein, the term "cryopreservative" is intended to mean a compound or material that, alone and/or in combination, protects the one or more tissues being irradiated during cooling or freezing. Illustrative examples of cryopreservatives include, but are not limited to, chondroitin sulfate, glycosaminoglycan dimethylsulfoxide, cell penetrating organic solutes, polysaccharides, glycerol, Dulbecco's minimum essential medium (DMEM), glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, DMSO, glycerol, trehalose, KH_2PO_4 , K_2HPO_4 , KCl, mannitol, NaHCO_3 , sodium ascorbate, 1,2-propanediol, formamide, 2,3-butanediol, probuchol, curcumin and mixtures thereof. Cryopreservatives may also act as stabilizers.

As used herein, the term "residual solvent content" is intended to mean the amount or proportion of freely-available liquid in the biological material. Freely-available liquid means the liquid, such as water and/or an organic solvent (e.g., ethanol, isopropanol, polyethylene glycol, etc.), present in the biological material being sterilized that is not bound to or complexed with one or more of the non-liquid components of the biological material. Freely-available liquid includes intracellular water and/or other solvents. The residual solvent contents related as water referenced herein refer to levels determined by the FDA approved, modified Karl Fischer method (Meyer and Boyd, Analytical Chem., 31:215-219, 1959; May, et al., *J. Biol. Standardization*, 10:249-259, 1982; Centers for Biologics Evaluation and Research, FDA, Docket No. 89D-0140, 83-93; 1990) or by near infrared spectroscopy. Quantitation of the residual levels of water or other solvents may be determined by means well known in the art, depending upon which solvent is employed. The proportion of residual solvent to solute may also be considered to be a reflection of the concentration of the solute within the solvent. When so expressed, the greater the concentration of the solute, the lower the amount of residual solvent.

As used herein, the term "sensitizer" is intended to mean a substance that selectively targets viruses, bacteria, in both vegetative and spore states, (including inter- and intracellular

bacteria, such as mycoplasmas, ureaplasmas, nanobacteria, chlamydia, rickettsias), yeasts, molds, fungi, single or multicellular parasites, and/or prions or similar agents responsible, alone or in combination, for TSEs, rendering them more sensitive to inactivation by radiation, therefore permitting the use of a lower rate or dose of radiation and/or a shorter time of irradiation than in the absence of the sensitizer. Illustrative examples of suitable sensitizers include, but are not limited to, the following: psoralen and its derivatives and analogs (including 3-carboethoxy psoralens); inactines and their derivatives and analogs; angelicins, khellins and coumarins which contain a halogen substituent and a water solubilization moiety, such as quaternary ammonium ion or phosphonium ion; nucleic acid binding compounds; brominated hematoporphyrin; phthalocyanines; purpurins; porphyrins; halogenated or metal atom-substituted derivatives of dihematoporphyrin esters, hematoporphyrin derivatives, benzoporphyrin derivatives, hydrodibenzoporphyrin dimaleimide, hydrodibenzoporphyrin, dicyano disulfone, tetracarbethoxy hydrodibenzoporphyrin, and tetracarbethoxy hydrodibenzoporphyrin dipropionamide; doxorubicin and daunomycin, which may be modified with halogens or metal atoms; netropsin; BD peptide, S2 peptide; S-303 (ALE compound); dyes, such as hypericin, methylene blue, eosin, fluoresceins (and their derivatives), flavins, merocyanine 540; photoactive compounds, such as bergapten; and SE peptide. In addition, atoms which bind to prions, and thereby increase their sensitivity to inactivation by radiation, may also be used. An illustrative example of such an atom would be the Copper ion, which binds to the prion protein and, with a Z number higher than the other atoms in the protein, increases the probability that the prion protein will absorb energy during irradiation, particularly gamma irradiation.

As used herein, the term "radiation" is intended to mean radiation of sufficient energy to sterilize at least some component of the irradiated biological material. Types of radiation include, but are not limited to, the following: (i) corpuscular (streams of subatomic particles such as neutrons, electrons, and/or protons); (ii) electromagnetic (originating in a varying electromagnetic field, such as radio waves, visible (both mono and polychromatic) and invisible light, infrared, ultraviolet radiation, x-radiation, and gamma rays and mixtures thereof); and (iii) sound and pressure waves. Such radiation is often described as either ionizing (capable of producing ions in irradiated materials) radiation, such as gamma rays, and non-ionizing radiation, such as visible light. The sources of such radiation may vary and, in general, the selection of a specific source of radiation is not critical provided that sufficient radiation is given in an appropriate time and at an appropriate rate to effect sterilization. In practice, gamma radiation is usually produced by isotopes of Cobalt or Cesium, while UV and X-rays are produced by machines that emit UV and X-radiation,

respectively, and electrons are often used to sterilize materials in a method known as "E-beam" irradiation that involves their production via a machine. Visible light, both mono- and polychromatic, is produced by machines and may, in practice, be combined with invisible light, such as infrared and UV, that is produced by the same machine or a different machine.

5 As used herein, the term "tissue" is intended to mean a substance derived or obtained from a multi-cellular living organism that performs one or more functions in the organism or a recipient thereof. Thus, as used herein, a "tissue" may be an aggregation of intercellular substance(s), such as collagen, elastin, fibronectin, fibrin, glycosaminoglycans and the like, and/or cells which are generally morphologically similar, such as hemapoietic cells, bone cells and the like. Accordingly, 10 the term "tissue" is intended to include both allogenic and autologous tissue, including, but not limited to, cellular viable tissue, cellular non-viable tissue and a cellular tissue, such as collagen, elastin, fibronectin, fibrin, glycosaminoglycans and the like. As used herein, the term "tissue" includes naturally occurring tissues, such as tissues removed from a living organism and used as such, or processed tissues, such as tissue processed so as to be less antigenic, for example 15 allogenic tissue intended for transplantation, and tissue processed to allow cells to proliferate into the tissue, for example demineralised bone matrix that has been processed to enable bone cells to proliferate into and through it or heart valves that have been processed to encourage cell engraftment following implantation. Additionally, as used herein, the term "tissue" is intended to include natural, artificial, synthetic, semi-synthetic or semi-artificial materials comprised of 20 biomolecules structured in such a way as to permit the replacement of at least some function(s) of a natural tissue when implanted into a recipient. Such constructs may be placed in a cell-containing environment prior to implantation to encourage their cellularization. Illustrative examples of tissues that may be treated according to the methods of the present invention include, but are not limited to, the following: connective tissue; epithelial tissue; adipose tissue; cartilage, bone 25 (including demineralised bone matrix); muscle tissue; and nervous tissue. Non-limiting examples of specific tissues that may be treated according to the methods of the present invention include heart, lung, liver, spleen, pancreas, kidney, corneas, joints, bone marrow, blood cells (red blood cells, leucocytes, lymphocytes, platelets, etc.), plasma, skin, fat, tendons, ligaments, hair, muscles, blood vessels (arteries, veins), teeth, gum tissue, fetuses, eggs (fertilized and not fertilized), eye 30 lenses, hands, nerve cells, nerves, and other physiologically and anatomically complex tissues, such as intestine, cartilage, entire limbs, cadavers, and portions of brain, and intracellular substances, such as collagen, elastin, fibrinogen, fibrin, fibronectin, glycosaminoglycans, and polysaccharides.

As used herein, the term "to protect" is intended to mean to reduce any damage to the biological material, such as one or more tissues, being irradiated, that would otherwise result from the irradiation of that material, to a level that is insufficient to preclude the safe and effective use of the material following irradiation. In other words, a substance or process "protects" a biological material, such as one or more tissues, from radiation if the presence of that substance or carrying out that process results in less damage to the material from irradiation than in the absence of that substance or process. Thus, a biological material, such as one or more tissues, may be used safely and effectively after irradiation in the presence of a substance or following performance of a process that "protects" the material, but could not be used with as great a degree of safety or as effectively after irradiation under identical conditions but in the absence of that substance or the performance of that process.

As used herein, an "acceptable level" of damage may vary depending upon certain features of the particular method(s) of the present invention being employed, such as the nature and characteristics of the particular one or more tissues and/or non-aqueous solvent(s) being used, and/or the intended use of the material being irradiated, and can be determined empirically by one skilled in the art. An "unacceptable level" of damage would therefore be a level of damage that would preclude the safe and effective use of the biological material, such as one or more tissues, being sterilized. The particular level of damage in a given biological material may be determined using any of the methods and techniques known to one skilled in the art.

B. Particularly Preferred Embodiments

A first preferred embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to said one or more tissues at least one stabilizer; and (ii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues, wherein said at least one stabilizer and the rate of irradiation are together effective to protect said one or more tissues from said radiation.

A second preferred embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to said one or more tissues at least one cryopreservative; and (ii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues.

A third preferred embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to said one or more tissues at least one stabilizer; (ii) subjecting said at least one tissue to a treatment effective to enhance penetration of said at least one stabilizer into said one or more tissues; and (iii) irradiating
5 said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues, wherein said at least one stabilizer and the rate of irradiation are together effective to protect said one or more tissue from said radiation.

A fourth preferred embodiment of the present invention is directed to a method for sterilizing one or more tissues that are sensitive to radiation, said method comprising: (i) adding to
10 said one or more tissues at least one cryopreservative; (ii) subjecting said one or more tissues to a treatment effective to enhance penetration of said at least one cryopreservative into said one or more tissues; and (iii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues.

Another preferred embodiment of the present invention is directed to a composition
15 comprising one or more tissues and at least one cryopreservative in an amount effective to preserve said one or more tissues for their intended use following sterilization with radiation.

According to certain embodiments of the present invention, the one or more tissues may contain a mixture of water and a non-aqueous solvent, such as ethanol and/or acetone. In such embodiments, the non-aqueous solvent(s) is (are) preferably a non-aqueous solvent that is not
20 prone to the formation of free-radicals upon irradiation, and most preferably a non-aqueous solvent that is not prone to the formation of free-radicals upon irradiation and that has little or no dissolved oxygen or other gas(es) that is (are) prone to the formation of free-radicals upon irradiation. Volatile non-aqueous solvents are particularly preferred, even more particularly preferred are non-aqueous solvents that are also stabilizers, such as ethanol and acetone.

The non-aqueous solvent is preferably a non-aqueous solvent that is not prone to the formation of free-radicals upon irradiation, and more preferably a non-aqueous solvent that is not prone to the formation of free-radicals upon irradiation and that has little or no dissolved oxygen or other gas(es) that is (are) prone to the formation of free-radicals upon irradiation. Volatile non-aqueous solvents are particularly preferred, even more particularly preferred are non-aqueous
25 solvents that are stabilizers, such as ethanol and acetone.
30

According to certain methods of the present invention, a stabilizer is added prior to irradiation of the one or more tissues with radiation. This stabilizer is preferably added to the one or

more tissues in an amount that is effective to protect the one or more tissues from the radiation. Alternatively, the stabilizer is added to the one or more tissues in an amount that, together with a non-aqueous solvent, is effective to protect the one or more tissues from the radiation. Suitable amounts of stabilizer may vary depending upon certain features of the particular method(s) of the present invention being employed, such as the particular stabilizer being used and/or the nature and characteristics of the particular one or more tissues being irradiated and/or its intended use, and can be determined empirically by one skilled in the art.

According to certain methods of the present invention, a cryopreservative is added prior to irradiation of the one or more tissues with radiation. This cryopreservative is preferably added to the one or more tissues in an amount that is effective to protect the one or more tissues during cooling or freezing. Suitable amounts of cryopreservatives may vary depending upon certain features of the particular method(s) of the present invention being employed, such as the particular cryopreservative being used and/or the nature and characteristics of the particular one or more tissues being irradiated and/or its intended use, and can be determined empirically by one skilled in the art. Illustrative examples of suitable cryopreservatives according to the present invention include chondroitin sulfate, glycosaminoglycan dimethylsulfoxide, cell penetrating organic solutes, polysaccharides, glycerol, Dulbecco's minimum essential medium, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, DMSO, glycerol, trehalose, KH_2PO_4 , K_2HPO_4 , KCl, mannitol, NaHCO_3 , sodium ascorbate, 1,2-propanediol, formamide, 2,3-butanediol, probuchol, curcumin and mixtures thereof. In a particularly preferred embodiment of the present invention, the cryopreservative comprises a mixture of Dulbecco's minimum essential medium, hepes buffer, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, chondroitin sulfate and DMSO.

According to certain methods of the present invention, the residual solvent content of the one or more tissues is reduced prior to irradiation of the one or more tissues with radiation. The residual solvent content is preferably reduced to a level that is effective to protect the one or more tissues from the radiation. Suitable levels of residual solvent content may vary depending upon certain features of the particular method(s) of the present invention being employed, such as the nature and characteristics of the particular one or more tissues being irradiated and/or its intended use, and can be determined empirically by one skilled in the art. There may be tissue for which it is desirable to maintain the residual solvent content to within a particular range, rather than a specific value.

According to certain embodiments of the present invention, when the one or more tissues also contain water, the residual solvent (water) content of one or more tissues may be reduced by dissolving or suspending the one or more tissues in a non-aqueous solvent that is capable of dissolving water. Preferably, such a non-aqueous solvent is not prone to the formation of free-radicals upon irradiation and has little or no dissolved oxygen or other gas(es) that is (are) prone to the formation of free-radicals upon irradiation.

While not wishing to be bound by any theory of operability, it is believed that the reduction in residual solvent content reduces the degrees of freedom of the one or more tissues, reduces the number of targets for free radical generation and may restrict the diffusability of these free radicals. Similar results might therefore be achieved by lowering the temperature of the one or more tissues below their eutectic point(s) or below their freezing point(s), or by vitrification to likewise reduce the degrees of freedom of the one or more tissues. These results may permit the use of a higher rate and/or dose of radiation than might otherwise be acceptable. Thus, the methods described herein may be performed at any temperature that doesn't result in unacceptable damage to the one or more tissues, *i.e.*, damage that would preclude the safe and effective use of the one or more tissues. Preferably, the methods described herein are performed at ambient temperature or below ambient temperature, such as below the eutectic point(s) or freezing point(s) of the one or more tissues being irradiated.

In certain embodiments of the present invention, the desired residual solvent content of a particular tissue may be found to lie within a range, rather than at a specific point. Such a range for the preferred residual solvent content of a particular tissue may be determined empirically by one skilled in the art.

The residual solvent content of the one or more tissues may be reduced by any of the methods and techniques known to those skilled in the art for reducing solvent from one or more tissues without producing an unacceptable level of damage to the one or more tissues. Such methods include, but are not limited to, lyophilization, drying, concentration, addition of alternative solvents, evaporation, chemical extraction, sonication induced nucleation and vitrification.

A particularly preferred method for reducing the residual solvent content of one or more tissues is lyophilization.

Another particularly preferred method for reducing the residual solvent content of one or more tissues is vitrification, which may be accomplished by any of the methods and techniques known to those skilled in the art, including the addition of solute and or additional solutes, such as

sucrose, to raise the eutectic point(s) of the one or more tissues, followed by a gradual application of reduced pressure to the one or more tissues in order to remove the residual solvent. The resulting glassy material will then have a reduced residual solvent content.

5 According to certain methods of the present invention, the one or more tissues to be sterilized may be immobilized upon or attached to a solid surface by any means known and available to one skilled in the art. For example, the one or more tissues to be sterilized may be attached to a biological or non-biological substrate.

10 The radiation employed in the methods of the present invention may be any radiation effective for the sterilization of the one or more tissues being treated. The radiation may be corpuscular, including E-beam radiation. Preferably the radiation is electromagnetic radiation, including x-rays, infrared, visible light, UV light and mixtures of various wavelengths of electromagnetic radiation. A particularly preferred form of radiation is gamma radiation.

15 According to the methods of the present invention, the one or more tissues are irradiated with the radiation at a rate effective for the sterilization of the one or more tissues, while not producing an unacceptable level of damage to the one or more tissues. Suitable rates of irradiation may vary depending upon certain features of the methods of the present invention being employed, such as the nature and characteristics of the particular tissue, which may contain a non-aqueous solvent, being irradiated, the particular form of radiation involved, and/or the particular biological contaminants or pathogens being inactivated. Suitable rates of irradiation can be determined
20 empirically by one skilled in the art. Preferably, the rate of irradiation is constant for the duration of the sterilization procedure. When this is impractical or otherwise not desired, a variable or discontinuous irradiation may be utilized.

25 According to the methods of the present invention, the rate of irradiation may be optimized to produce the most advantageous combination of product recovery and time required to complete the operation. Both low (≤ 3 kGy/hour) and high (> 3 kGy/hour) rates may be utilized in the methods described herein to achieve such results. The rate of irradiation is preferably selected to optimize the recovery of the one or more tissues while still sterilizing the one or more tissues. Although reducing the rate of irradiation may serve to decrease damage to the one or more tissues, it will also result in longer irradiation times being required to achieve a particular desired total dose. A
30 higher dose rate may therefore be preferred in certain circumstances, such as to minimize logistical issues and costs, and may be possible particularly when used in accordance with the methods described herein for protecting tissue from irradiation.

According to a particularly preferred embodiment of the present invention, the rate of irradiation is not more than about 3.0 kGy/hour, more preferably between about 0.1 kGy/hr and 3.0 kGy/hr, even more preferably between about 0.25 kGy/hr and 2.0 kGy/hour, still even more preferably between about 0.5 kGy/hr and 1.5 kGy/hr and most preferably between about 0.5 kGy/hr and 1.0 kGy/hr.

According to another particularly preferred embodiment of the present invention, the rate of irradiation is at least about 3.0 kGy/hr, more preferably at least about 6 kGy/hr, even more preferably at least about 16 kGy/hr, even more preferably at least about 30 kGy/hr and most preferably at least about 45 kGy/hr or greater.

According to the methods of the present invention, the one or more tissues to be sterilized are irradiated with the radiation for a time effective for the sterilization of the one or more tissues. Combined with irradiation rate, the appropriate irradiation time results in the appropriate dose of irradiation being applied to the one or more tissues. Suitable irradiation times may vary depending upon the particular form and rate of radiation involved and/or the nature and characteristics of the particular one or more tissues being irradiated. Suitable irradiation times can be determined empirically by one skilled in the art.

According to the methods of the present invention, the one or more tissues to be sterilized are irradiated with radiation up to a total dose effective for the sterilization of the one or more tissues, while not producing an unacceptable level of damage to those one or more tissues. Suitable total doses of radiation may vary depending upon certain features of the methods of the present invention being employed, such as the nature and characteristics of the particular one or more tissues being irradiated, the particular form of radiation involved, and/or the particular biological contaminants or pathogens being inactivated. Suitable total doses of radiation can be determined empirically by one skilled in the art. Preferably, the total dose of radiation is at least 25 kGy, more preferably at least 45 kGy, even more preferably at least 50 kGy, still more preferably at least 75 kGy and still even more preferably at least 100 kGy or greater, such as 150 kGy or 200 kGy or greater.

The particular geometry of the one or more tissues being irradiated, such as the thickness and distance from the source of radiation, may be determined empirically by one skilled in the art. A preferred embodiment is a geometry that provides for an even rate of irradiation throughout the preparation of one or more tissues. A particularly preferred embodiment is a geometry that results in a short path length for the radiation through the preparation, thus minimizing the differences in

radiation dose between the front and back of the preparation. This may be further minimized in some preferred geometries, particularly those wherein the preparation of one or more tissues has a relatively constant radius about its axis that is perpendicular to the radiation source and by the utilization of a means of rotating the preparation of one or more tissues about said axis. In a particularly preferred embodiment of the present invention, the tissue is irradiated in an arc centered about the radiation source.

Similarly, according to certain methods of the present invention, an effective package for containing the preparation of one or more tissues during irradiation is one which combines stability under the influence of irradiation, and which minimizes the interactions between the package of one or more tissues and the radiation. Preferred packages maintain a seal against the external environment before, during and post-irradiation, and are not reactive with the preparation of one or more tissues within, nor do they produce chemicals that may interact with the preparation of one or more tissues within. Particularly preferred examples include but are not limited to containers that comprise glasses stable when irradiated, stoppered with stoppers made of rubber or other suitable materials that is relatively stable during radiation and liberates a minimal amount of compounds from within, and sealed with metal crimp seals of aluminium or other suitable materials with relatively low Z numbers. Suitable materials can be determined by measuring their physical performance, and the amount and type of reactive leachable compounds post-irradiation, and by examining other characteristics known to be important to the containment of such biological materials as tissue empirically by one skilled in the art.

Similarly, in certain preferred embodiments of the present invention, "terminal sterilization" is carried out. That is, the one or more tissues are packaged prior to irradiation in a package that is impervious to pathogens. Following treatment according to the present invention, the one or more tissues may be distributed safely without contamination or degradation. Thus, as used herein, the phrase "packaged prior to sterilization" includes terminal sterilization.

According to certain methods of the present invention, an effective amount of at least one sensitizing compound may optionally be added to the one or more tissues prior to irradiation, for example to enhance the effect of the irradiation on the biological contaminant(s) or pathogen(s) therein, while employing the methods described herein to minimize the deleterious effects of irradiation upon the one or more tissues. Suitable sensitizers are known to those skilled in the art, and include psoralens and their derivatives, riboflavins and their derivatives and inactines and their derivatives.

According to the methods of the present invention, the irradiation of the one or more tissues may occur at any temperature that is not deleterious to the one or more tissues being sterilized. According to one preferred embodiment, the one or more tissues are irradiated at ambient temperature. According to an alternate preferred embodiment, the one or more tissues are irradiated at reduced temperature, , *i.e.*, a temperature below ambient temperature, such as by cooling on dry ice, liquid nitrogen or combinations thereof. Preferred temperatures below ambient temperature according to the present invention include 0°C, -20°C, -40°C, -60°C, -78°C or -196°C. According to this embodiment of the present invention, the one or more tissues are preferably irradiated at or below the freezing or eutectic point(s) of the one or more tissues or the residual solvent therein. According to another alternate preferred embodiment, the one or more tissues are irradiated at elevated temperature, *i.e.*, a temperature above ambient temperature, such as 37°C, 60°C, 72°C or 80°C. While not wishing to be bound by any theory, the use of elevated temperature may enhance the effect of irradiation on the biological contaminant(s) or pathogen(s) and therefore allow the use of a lower total dose of radiation.

Most preferably, the irradiation of the one or more tissues occurs at a temperature that protects the preparation of one or more tissues from radiation. Suitable temperatures can be determined empirically by one skilled in the art.

In certain embodiments of the present invention, the temperature at which irradiation is performed may be found to lie within a range, rather than at a specific point. Such a range for the preferred temperature for the irradiation of a particular tissue may be determined empirically by one skilled in the art.

According to the methods of the present invention, the irradiation of the one or more tissues may occur at any pressure which is not deleterious to the one or more tissues being sterilized. According to one preferred embodiment, the one or more tissues are irradiated at elevated pressure. More preferably, the one or more tissues are irradiated at elevated pressure due to the application of sound waves or the use of a volatile. While not wishing to be bound by any theory, the use of elevated pressure may enhance the effect of irradiation on the biological contaminant(s) or pathogen(s) and/or enhance the protection afforded by one or more stabilizers, and therefore allow the use of a lower total dose of radiation. Suitable pressures can be determined empirically by one skilled in the art.

Generally, according to the methods of the present invention, the pH of the one or more tissues undergoing sterilization is about 7. In some embodiments of the present invention,

however, the one or more tissues may have a pH of less than 7, preferably less than or equal to 6, more preferably less than or equal to 5, even more preferably less than or equal to 4, and most preferably less than or equal to 3. In alternative embodiments of the present invention, the one or more tissues may have a pH of greater than 7, preferably greater than or equal to 8, more preferably greater than or equal to 9, even more preferably greater than or equal to 10, and most preferably greater than or equal to 11. According to certain embodiments of the present invention, the pH of the preparation of one or more tissues undergoing sterilization is at or near the isoelectric point of one of the components of the one or more tissues. Suitable pH levels can be determined empirically by one skilled in the art.

10 Similarly, according to the methods of the present invention, the irradiation of the one or more tissues may occur under any atmosphere that is not deleterious to the one or more tissues being treated. According to one preferred embodiment, the one or more tissues are held in a low oxygen atmosphere or an inert atmosphere. When an inert atmosphere is employed, the atmosphere is preferably composed of a noble gas, such as helium or argon, more preferably a
15 higher molecular weight noble gas, and most preferably argon. According to another preferred embodiment, the one or more tissues are held under vacuum while being irradiated. According to a particularly preferred embodiment of the present invention, the one or more tissues (lyophilized, liquid or frozen) are stored under vacuum or an inert atmosphere (preferably a noble gas, such as helium or argon, more preferably a higher molecular weight noble gas, and most preferably argon)
20 prior to irradiation. According to an alternative preferred embodiment of the present invention, the one or more tissues are held under low pressure, to decrease the amount of gas, particularly oxygen and nitrogen, dissolved in the liquid, prior to irradiation, either with or without a prior step of solvent reduction, such as lyophilization. Such degassing may be performed using any of the methods known to one skilled in the art. For example, the one or more tissues may be treated prior
25 to irradiation with at least one cycle, and preferably three cycles, of being subjected to a vacuum and then being placed under an atmosphere comprising at least one noble gas, such as argon, or nitrogen.

30 In another preferred embodiment, where the one or more tissues contain oxygen or other gases dissolved within the one or more tissues or within their container or associated with them, the amount of these gases within or associated with the preparation of one or more tissues may be reduced by any of the methods and techniques known and available to those skilled in the art, such as the controlled reduction of pressure within a container (rigid or flexible) holding the preparation

of one or more tissues to be treated or by placing the preparation of one or more tissues in a container, of approximately equal volume to the tissue, i.e., leaving no head space.

In certain embodiments of the present invention, when the one or more tissues to be treated contains an aqueous or non-aqueous solvent, or a mixture of such solvents, at least one stabilizer is introduced according to any of the methods and techniques known and available to one skilled in the art, including soaking the tissue in a solution containing the stabilizer(s), preferably under pressure, at elevated temperature and/or in the presence of a penetration enhancer, such as dimethylsulfoxide, and more preferably, when the stabilizer(s) is a protein, at a high concentration. Other methods of introducing at least one stabilizer into tissue include, but are not limited to, the following: applying a gas containing the stabilizer(s), preferably under pressure and/or at elevated temperature; injecting the stabilizer(s) or a solution containing the stabilizer(s) directly into the tissue; placing the tissue under reduced pressure and then introducing a gas or solution containing the stabilizer(s); dehydrating the tissue, such as by using a buffer of high ionic and/or osmolar strength, and rehydrating the tissue with a solution containing the stabilizer(s); applying a high ionic strength solvent containing the stabilizer(s), which may optionally be followed by a controlled reduction in the ionic strength of the solvent; cycling the tissue between solutions of high ionic and/or osmolar strength and solutions of low ionic and/or osmolar strength containing the stabilizer(s); applying the at least one stabilizer within or as a component of a microemulsion; and combinations of two or more of these methods. One or more sensitizers may also be introduced into tissue according to such methods.

In certain embodiments of the present invention, at least one cryopreservative is introduced into the one or more tissues according to any of the methods and techniques known and available to one skilled in the art, including soaking the tissue in a solution containing the cryopreservative(s), preferably under pressure, at elevated temperature and/or in the presence of a penetration enhancer, such as dimethylsulfoxide, and more preferably. Other methods of introducing at least one cryopreservative into tissue include, but are not limited to, the following: applying a gas containing the cryopreservative(s), preferably under pressure and/or at elevated temperature; injecting the cryopreservative(s) or a solution containing the cryopreservative(s) directly into the tissue; placing the tissue under reduced pressure and then introducing a gas or solution containing the cryopreservative(s); dehydrating the tissue, such as by using a buffer of high ionic and/or osmolar strength, and rehydrating the tissue with a solution containing the cryopreservative(s); applying a high ionic strength solvent containing the cryopreservative(s), which may optionally be followed by a controlled reduction in the ionic strength of the solvent; cycling the tissue between

solutions of high ionic and/or osmolar strength and solutions of low ionic and/or osmolar strength containing the cryopreservative(s); applying the at least one cryopreservative within or as a component of a microemulsion; and combinations of two or more of these methods. One or more sensitizers may also be introduced into tissue according to such methods.

- 5 According to certain preferred embodiments of the present invention, the one or more tissues may be subjected to a treatment effective to enhance penetration of the one or more stabilizers and/or cryopreservatives and/or sensitizers into the tissue. Such treatments include physical treatments and chemical treatments.

- 10 For instance, with respect to chemical treatment, the tissue may be treated with one or more compounds that cause an increase in the distance between molecules in the tissue, thereby promoting penetration of the stabilizers and/or cryopreservatives and/or sensitizers into the one or more tissues. Alternatively, the chemical treatment may include treating the one or more tissues with a microemulsion effective to enhance penetration of the stabilizers and/or cryopreservatives and/or sensitizers into the one or more tissues.

- 15 Similarly, the tissue may be treated with one or more compounds that cause macromolecules in the tissue to become less compact, or relaxed, thereby promoting penetration of the stabilizer(s) and/or cryopreservatives and/or sensitizer(s) into the tissue or providing a greater surface area of tissue to be in contact with the stabilizer(s) and/or cryopreservatives and/or sensitizer(s). The compounds that cause macromolecules in the tissue to become less compact, or relaxed, may also be applied prior to introduction of the stabilizer(s) and/or cryopreservatives and/or sensitizer(s), which may then be introduced in a similar solution followed by application of a solution containing a similar amount of stabilizer(s) and/or cryopreservatives and/or sensitizer(s) but a reduced amount of the compounds that cause macromolecules in the tissue to become less compact, or relaxed. Repeated applications of such solutions, with progressively lower amounts of compounds that cause macromolecules in the tissue to become less compact, or relaxed, may subsequently be applied.

The compounds that promote penetration may be used alone or in combination, such as a combination of a compound that causes macromolecules in the tissue to become less compact and a compound that causes an increase in the distance between molecules in the tissue.

- 30 Further, in those embodiments of the present invention wherein the stabilizer(s) and/or cryopreservatives and/or sensitizer(s) is cationic, one or more anionic compounds may be added to the solution containing the stabilizer(s) and/or cryopreservatives and/or sensitizer(s) prior to and/or

during application thereof to the tissue. The anionic compound(s) may also be applied prior to introduction of the stabilizer(s) and/or cryopreservatives and/or sensitizer(s), which may then be introduced in a similar solution followed by application of a solution containing a similar amount of stabilizer(s) and/or cryopreservatives and/or sensitizer(s) but a reduced amount of the anionic compound(s). Repeated applications of such solutions, with progressively lower amounts of anionic compound(s) may subsequently be applied.

Similarly, in those embodiments of the present invention wherein the stabilizer(s) and/or cryopreservatives and/or sensitizer(s) is anionic, one or more cationic compounds may be added to the solution containing the stabilizer(s) and/or cryopreservatives and/or sensitizer(s) prior to and/or during application thereof to the tissue. The cationic compound(s) may also be applied prior to introduction of the stabilizer(s) and/or cryopreservatives and/or sensitizer(s), which may then be introduced in a similar solution followed by application of a solution containing a similar amount of stabilizer(s) and/or cryopreservatives and/or sensitizer(s) but a reduced amount of the cationic compound(s). Repeated applications of such solutions, with progressively lower amounts of cationic compound(s) may subsequently be applied.

Regarding physical treatments effective to enhance penetration of the one or more stabilizer(s) and/or cryopreservative(s) and/or sensitizer(s) into the tissue, examples include, but are not limited to, physical agitation, such as by shaking or sonication, slow freezing and fast freezing.

According to embodiments of the present invention employing physical agitation, such as sonication or shaking, physical agitation is carried out for a time effective to enhance penetration of the one or more stabilizer(s) and/or cryopreservative(s) and/or sensitizer(s) into the tissue. The duration of such treatment will depend upon, among other factors, the nature of the one or more tissues, the nature of the solvent(s) employed, and the nature of the one or more stabilizer(s) and/or cryopreservative(s) and/or sensitizer(s). Suitable times may easily be determined empirically by one having ordinary skill in the art.

Fast freezing is typically carried out in a relatively short period of time, preferably less than about 15 minutes, more preferably less than about 10 minutes, even more preferably about 5 minutes, still more preferably less than about 5 minutes and most preferably less than about 1 minute. Fast freezing may be carried out, for instance, by placing the one or more tissues in a cold bath, such as, for example, dry-ice/ethanol, dry ice/acetone, dry-ice/methanol and the like, or exposing one or more tissues to the liquid phase of a gas that liquifies at low temperature or its

vapor, such as liquified nitrogen, or to the solid phase of a gas that solidifies at a low temperature, such as carbon dioxide (as "dry ice") or a suitable mixture of two or more of the treatments described herein.

5 In embodiments of the present invention employing slow freezing, the temperature of the tissue is gradually lowered over a prolonged period of time, for instance from about one-half hour to about 2 hours, preferably about one hour, at a rate of from about 0.5 to about 2.5°C/min. Preferably, the rate is from about 0.5 to about 1.5°C/min, more preferably about 0.5 to about 1.0°C/min and most preferably about 1°C/min.

10 In addition to enhancing penetration of the stabilizers and/or cryopreservatives and/or sensitizers, the treatments described above may also enhance cleaning of the one or more tissues. That is, by treatment as set forth above with respect to penetration enhancement, the physical and chemical treatments are effective to clean the one or more tissues and remove infected or undesirable material therefrom. For instance, bone may be subjected to physical treatment, e.g., sonication, and/or chemical treatment, e.g., treatment with a microemulsion, to remove marrow and
15 other residual residues therefrom. In this way, components that might give rise to infection or contamination may effectively be eliminated.

It will be appreciated that the combination of one or more of the features described herein may be employed to further minimize undesirable effects upon the one or more tissues caused by irradiation, while maintaining adequate effectiveness of the irradiation process on the biological
20 contaminant(s) or pathogen(s). For example, in addition to the use of a stabilizer, a particular tissue may also be lyophilized, held at a reduced temperature and kept under vacuum prior to irradiation to further minimize undesirable effects.

The sensitivity of a particular biological contaminant or pathogen to radiation is commonly calculated by determining the dose necessary to inactivate or kill all but 37% of the agent in a
25 sample, which is known as the D_{37} value. The desirable components of a tissue may also be considered to have a D_{37} value equal to the dose of radiation required to eliminate all but 37% of their desirable biological and physiological characteristics.

In accordance with certain preferred methods of the present invention, the sterilization of one or more tissues is conducted under conditions that result in a decrease in the D_{37} value of the
30 biological contaminant or pathogen without a concomitant decrease in the D_{37} value of the one or more tissues. In accordance with other preferred methods of the present invention, the sterilization of one or more tissues is conducted under conditions that result in an increase in the D_{37} value of

the tissue material. In accordance with the most preferred methods of the present invention, the sterilization of one or more tissues is conducted under conditions that result in a decrease in the D_{37} value of the biological contaminant or pathogen and a concomitant increase in the D_{37} value of the one or more tissues.

- 5 In accordance with certain preferred methods of the present invention, the sterilization of one or more tissues is conducted under conditions that reduce the possibility of the production of neo-antigens. In accordance with other preferred embodiments of the present invention, the sterilization of one or more tissues is conducted under conditions that result in the production of substantially no neo-antigens. Additionally, in accordance with other preferred embodiments of the present invention, the neo-antigen formation may be reduced relative to tissues not treated according to the present invention. The present invention also includes tissues sterilized according to such methods.
- 10

- In accordance with certain preferred methods of the present invention, the sterilization of one or more tissues is conducted under conditions that reduce the total antigenicity of the tissue(s).
- 15 In accordance with other preferred embodiments of the present invention the sterilization of one or more tissues is conducted under conditions that reduce the number of reactive allo-antigens and/or xeno-antigens in the tissue(s). The present invention also includes tissues sterilized according to such methods.

- A particularly preferred tissue for use with the methods of the present invention is collagen.
- 20 According to certain embodiments of the present invention, collagen is employed as a model tissue for determining optimal conditions, such as preferred rates of irradiation, temperatures, residual solvent content, and the like, for sterilizing a given tissue type with gamma radiation without rendering the tissue unsafe and/or ineffective for its intended purpose. Thus, another preferred embodiment of the present invention is directed to an assay for determining the optimal conditions for sterilizing a tissue that contains collagen without adversely affecting a predetermined biological characteristic or property thereof, which comprises the steps of: (i) irradiating collagen under a pre-determined set of conditions effective to sterilize the tissue ; (ii) determining the turbidity of the irradiated collagen; and (iii) repeating steps (i) and (ii) with a different pre-determined set of conditions until the turbidity of the irradiated collagen reaches a pre-determined acceptable level.
- 25

- 30 According to certain preferred embodiments of the present invention, one or more tissues sterilized according to the methods described herein may be introduced into a mammal in need

thereof for prophylaxis or treatment of a condition or disease or malfunction or deficit of a tissue. Methods of introducing such tissue into a mammal are known to those skilled in the art.

When employed in such embodiments, one or more tissues sterilized according to the methods described herein do not produce sufficient negative characteristics in the tissue(s) following introduction into the mammal to render the tissue(s) unsafe and/or ineffective for the intended use thereof. Illustrative examples of such negative characteristics include, but are not limited to, inflammation and calcification. Such negative characteristics may be detected by any means known to those skilled in the art, such as MRIs, CAT scans and the like.

Tissues treated according to the present invention are likely to have a decreased incidence of rejection in a recipient, since pathogens and other contaminants are either reduced or eliminated by practicing the present invention. There may also be a reduction in the number or magnitude of the response provoked by alloantigens and/or neoantigens. Additionally, tissues treated according to the present invention, for instance heart valves and ligaments, are likely to show less calcification than those not treated according to the present invention. Moreover, tissues treated according to the methods of the present invention are likely to exhibit lower toxicity and mutagenicity than tissues not so treated.

According to particularly preferred embodiments of the present invention, sterilization of the one or more tissues is conducted after the tissue(s) is packaged, i.e. as a terminal sterilization process.

Examples

The following examples are illustrative, but not limiting, of the present invention. Other suitable modifications and adaptations are of the variety normally encountered by those skilled in the art and are fully within the spirit and scope of the present invention. For example, heart valves from animal species other than pig, such as bovine or human, are encompassed by this technology, as are heart valves from transgenic mammals. In addition, heart valves prepared/modified by practice of the present invention may be used for transplantation into any animal, particularly into mammals. Furthermore, the principles of the technology of the present invention may be practiced on animal tissues and organs other than heart valves. Unless otherwise noted, all irradiation was accomplished using a ^{60}Co source.

Example 1

In this experiment, porcine heart valves were gamma irradiated in the presence of polypropylene glycol 400 (PPG400) and, optionally, a scavenger, to a total dose of 30 kGy (1.584 kGy/hr at -20°C).

5 Materials:

Tissue – Porcine Pulmonary Valve (PV) Heart valves were harvested prior to use and stored.

Tissue Preparation Reagents -

Polypropylene Glycol 400. Fluka: cat# 81350, lot# 386716/1

10 Trolox C. Aldrich: cat# 23,881-3, lot# 02507TS

Coumaric Acid. Sigma: cat# C-9008, lot# 49H3600

n-Propyl Gallate. Sigma: cat# P-3130, lot# 117H0526

D-Lipoic Acid. CalBiochem: cat# 437692, lot# B34484

Dulbecco's PBS. Gibco BRL: cat# 14190-144, lot# 1095027

15 2.0 ml Screw Cap tubes. VWR Scientific Products: cat# 20170-221, lot# 0359

Tissue Hydrolysis Reagents -

Nerl H₂O. NERL Diagnostics: cat# 9800-5, lot# 03055151

Acetone. EM Science: cat# AX0125-5, lot# 37059711

6 N constant boiling HCl. Pierce: cat# 24309, lot# BA42184

20 Int-Pyd (Acetylated Pyridinoline) HPLC Internal Standard. Metra Biosystems Inc.: cat# 8006,

lot# 9H142, expiration 2/2002, Store at -20°C

Hydrochloric Acid. VWR Scientific: cat# VW3110-3, lot# n/a

Heptafluorobutyric Acid (HFBA) Sigma: cat# H-7133, lot# 20K3482

25 FW 214.0 store at 2-8°C

SP-Sephadex C-25 resin. Pharmacia: cat# 17-0230-01, lot# 247249 (was charged with NaCl as per manufacturer suggestion)

Hydrolysis vials - 10 mm x 100 mm vacuum hydrolysis tubes. Pierce: cat# 29560, lot #BB627281

30 Heating module - Pierce, Reacti-therm.: Model # 18870, S/N 1125000320176

Savant - Savant Speed Vac System

Speed Vac Model SC110, model # SC110-120, serial # SC110-SD171002-1H

a. Refrigerated Vapor Trap Model RVT100, model # RVT100-120V, serial # RVT100-58010538-1B

b. Vacuum pump, VP 100 Two Stage Pump Model VP100, serial # 93024

Column - Phenomenex, Luna 5 μ C18(2) 100 Å, 4.6 x 250 mm. Part # 00G-4252-E0, S/N# 68740-

5 25, B/N# 5291-29

PLC System: Shimadzu System Controller SCL-10A

Shimadzu Automatic Sample Injector SIL-10A (50 μ loop)

Shimadzu Spectrofluorometric Detector RF-10A

Shimadzu Pumps LC-10AD

10 Software – Class-VP version 4.1

Low-binding tubes - MiniSorp 100 x15 Nunc-Immuntube. Batch # 042950, cat# 468608

Methods:

A. Preparation of stabilizer solutions:

15 **Trolox C:**

The 0.5 M solution was not soluble; therefore additional PPG was added. After water bath sonication at 25°C and above for at least 30 minutes, Trolox C is soluble at 125 mM.

Coumaric Acid:

20 Water bath sonicated at 25°C and above for approximately 15 minutes – not 100 % soluble. An additional 1 ml PPG was added and further water bath sonicated.

n-Propyl Gallate:

The 0.5M solution was soluble after a 20-30 minute water bath sonication.

25

1 M Lipoic Acid:

Very soluble after 10 minute water bath sonication.

30

Final Stocks of Scavengers:

125 mM Trolox C - 4 ml

0.5 M Coumaric acid - 2 ml

0.5 M n-Propyl Gallate - 2 ml

1 M Lipoic Acid - 2 ml

B. Treatment of valves prior to gamma-irradiation.

1. PV heart valves were thawed on wet ice.
2. Cusps were dissected out from each valve and pooled into 50 ml conical tubes
5. containing cold Dulbecco's PBS.
3. Cusps were washed in PBS at 4°C for approximately 1.5 hrs; changing PBS during that time a total of 6 times.
4. 2 cusps were placed in each of six 2 ml screw cap tube.
5. 1.2 ml of PPG were added to two tubes (one of these tubes was designated 0 kGy and
- 10 the other tube was designated 30 kGy):
 - 1.2 ml of 125 mM Trolox C in PPG were added to another two tubes
 - 1.2 ml of SCb stabilizer mixture – comprising of 1.5 ml 125 mM Trolox C, 300 µl 1 M Lipoic Acid, 600 µl 0.5 M Coumaric Acid and 600 µl 0.5 M n-Propyl Gallate (Final concentrations: 62.5 mM, 100 mM, 100 mM and 100 mM respectively) were added to the final two tubes.
- 15 6. Tubes were incubated at 4°C, with rocking for about 60 hours.
7. Stabilizer solutions and cusps were transferred into 2 ml glass vials for gamma-irradiation.
8. All vials were frozen on dry ice.
9. Control samples were kept in-house at -20°C.

C. Gamma-irradiation of tissue.

Samples were irradiated at a rate of 1.584 kGy/hr at -20°C to a total dose of 30 kGy.

D. Processing tissue for Hydrolysis/Extraction.

1. Since PPG is viscous, PBS was added to allow for easier transfer of material.
2. Each pair of cusps (2 per condition) were placed into a 50 ml Falcon tube filled with cold PBS and incubated on ice – inverting tubes periodically.
3. After one hour PBS was decanted from the tubes containing cusps in PPG/0kGy and PPG/30kGy and replenished with fresh cold PBS. For the PPG samples containing Trolox C or
- 30 SCb stabilizer mixture, fresh 50 ml Falcon tubes filled with cold PBS were set-up and the cusps transferred.
4. An additional 3 washes were done.

5. One cusp was transferred into a 2 ml Eppendorf tube filled with cold PBS for extraction. The other cusp was set-up for hydrolysis.

E. Hydrolysis of tissue.

- 5 1. Each cusp was washed 6x with acetone in an Eppendorf tube (approximately 1.5 ml/wash).
2. Each cusp was subjected to SpeedVac (with no heat) for approximately 15 minutes or until dry.
3. Samples were weighed, transferred to hydrolysis vials and 6 N HCl added at a volume
- 10 of 20 mg tissue/ml HCl:

	<u>Sample ID</u>	<u>Dry Weight (mg)</u>	<u>μl 6 N HCl</u>
	1. PPG/0	6.49	325
	2. PPG/30	7.26	363
15	3. PPG T/0	5.80	290
	4. PPG T/30	8.20	410
	5. PPG SCb/0	6.41	321
	6. PPG SCb/30	8.60	430

- 20 4. Samples were hydrolyzed at 110 °C for approximately 23 hours.
 5. Hydrolysates were transferred into Eppendorf tubes and centrifuged @ 12,000 rpm for 5 min.
 6. Supernatant was then transferred into a clean Eppendorf.
 7. 50 μl of hydrolysate was diluted in 8ml Nerl H₂O (diluting HCl to approximately 38 mM).
 - 25 8. Spiked in 200 μl of 2x int-pyd. Mixed by inversion. (For 1600 μl 2x int-pyd:160 μl 20x int-pyd + 1440 μl Nerl H₂O.)
 9. Samples were loaded onto SP-Sephadex C25 column (approximately 1 x 1 cm packed bed volume) that had been equilibrated in water. (Column was pre-charged with NaCl)
 10. Loaded flow through once again over column.
 - 30 11. Washed with 20 ml 150 mM HCl.
 12. Eluted crosslinks with 5 ml 2 N HCl into a low binding tube. 13.
- Dried entire sample in Savant.

F. Analysis of hydrolysates.

Set-up the following:

Sample	μ l	μ l H ₂ O	μ l HFBA
1. PPG/0 kGy	18	180	2
2. PPG/30 kGy	59	139	2
3. PPG T/0 kGy	67	171	2
4. PPG T/30 kGy	64	134	2
5. PPG SCb/0 kGy	10	188	2
6. PPG SCb/30 kGy	32	166	2

Results:

The HPLC results are shown in Figures 1A-1C. In the presence of PPG 400, the results were nearly identical whether the heart valve had been irradiated or not. The addition of a single stabilizer (Irolox C) or a stabilizer mixture produced even more effective results. The gel analysis, shown in Figure 1D, confirmed the effectiveness of the protection provided by these conditions.

Example 2

In this experiment, the effects of gamma irradiation were determined on porcine heart valve cusps in the presence of 50% DMSO and, optionally, a stabilizer, and in the presence of polypropylene glycol 400 (PPG400).

Preparation of tissue for irradiation:

1. 5 vials of PV and 3 vials of atrial valves (AV) were thawed on ice.
2. Thaw media was removed and valves rinsed in beaker filled with PBS.
3. Transferred each valve to 50 ml conical containing PBS. Washed by inversion and removed.
4. Repeated wash 3 times.
5. Dissected out the 3 cusps (valves).
6. Stored in PBS in 2 ml screw top Eppendorf Vials (Eppendorfs) and kept on ice.

Preparation of stabilizers:

All stabilizers were prepared so that the final concentration of DMSO was 50 %.

1 M Ascorbate in 50 % DMSO:

Aldrich: cat# 26,855-0, lot# 10801HU

200 mg dissolved in 300 μ l H₂O. Add 500 μ l DMSO. The volume was adjusted to 1 ml with H₂O. Final pH was 8.0.

5

1 M Coumaric Acid:

Sigma: cat# C-9008, lot# 49H3600. MW 164.2

Dissolve 34.7 mg in 106 μ l DMSO, pH 3.0

138 μ l H₂O was added. Sample precipitated out of solution.

10

Coumaric went back into solution once pH was adjusted to 7.5 with 1 N NaOH.

1 M n-Propyl Gallate:

Sigma: cat# P-3130, lot# 117H0526. MW 212.2

Dissolve 58.2 mg in 138 μ l DMSO.

Add 138 μ l H₂O. Final pH is 6.5 or slightly lower.

15

Stabilizer Mixture (SM-a):

1.0 ml 500 mM Ascorbate

500 μ l 1 M Coumaric Acid

300 μ l 1 M n-propyl gallate

20

1.2 ml 50 % DMSO

3.0 ml

Method:

25

1.6 ml of a solution (stabilizer mixture or PPG400) was added to each sample and then the sample was incubated at 4°C for 2.5 days. Valves and 1 ml of the solution in which they were incubated were then transferred into 2 ml irradiation vials. Each sample was irradiated with gamma irradiation at a rate of 1.723 kGy/hr at 3.6°C to a total dose of 25 kGy.

Hydrolysis of tissue:

30

1. Washed each cusp 6 times with acetone in a 2 ml Eppendorf Vial.
2. After final acetone wash, dried sample in Savant (without heat) for approximately 10-15 minutes or until dry.

3. Weighed the samples, transferred them to hydrolysis vials and then added 6 N HCl at a volume of 20 mg tissue/ml HCl:

	<u>Sample ID</u>	<u>Dry Weight (mg)</u>	<u>μl 6 N HCl</u>
5	1. PBS/0 kGy	11.4	570
	2. PBS /25kGy	6.0	300
	3. DMSO/0kGy	6.42	321
	4. DMSO/25kGy	8.14	407
	5. DMSO/SM-a/0kGy	8.7	435
10	6. DMSO/SM-a/25kGy	8.15	408
	7. PPG/0kGy	13.09	655
	8. PPG/25kGy	10.88	544

SM = Stabilizer Mixture as defined above.

5. Samples were hydrolyzed at 110 °C for approximately 23 hours.

15 6. Hydrolysates were transferred into Eppendorf vials and centrifuged at 12,000 rpm for 5 min.

7. Supernatant was transferred into a clean Eppendorf vial.

8. 50 μl hydrolysate was diluted in 8ml Nerl H₂O (diluting HCl to approximately 37 mM).

20 9. Spiked in 200 μl of 2x int-pyd. Mixed by inversion. (For 2000 μl 2x int-pyd: 200 μl 20x int-pyd + 1.8 ml Nerl H₂O.)

10. Samples were loaded onto SP-Sephadex C25 column (approximately 1x1 cm packed bed volume) that had been equilibrated in water. (Column was pre-charged with NaCl)

11. Loaded flow through once again over column.

12. Washed with 20 ml 150 mM HCl.

25 13. Eluted crosslinks with 5 ml 2 N HCl into a low binding tube. 50 ml 2 N HCl:8.6 ml concentrated HCl adjusted to a volume of 50 ml with Nerl H₂O.

14. Dried entire sample in Savant.

Guanidine HCl Extraction and DEAE-Sepharose Purification of Proteoglycans:

30 4M Guanidine HCl Extraction:

1. Removed all three cusps from gamma irradiation vial and transferred to separate 50ml conical tube.

2. Washed cusps five times with 50ml dPBS (at 4°C over approx. 5 hours) and determined wet weight of one cusp after drying on Kimwipe.

3. Transferred one cusp from each group to 1.5ml microfuge tube and added appropriate volume of 4M guanidine HCl/150mM sodium acetate buffer pH 5.8 with 2µg/ml protease inhibitors (aprotinin, leupeptin, pepstatin A) to have volume to tissue ratio of 15 (see Methods in Enzymology Vol. 144 p.321 – for optimal yield use ratio of 15 to 20).

4. Diced cusps into small pieces with scissors.

5. Nutated at 4°C for ~48hours.

6. Centrifuged at 16,500 RPM on Hermle Z-252M, at 4°C for 10min.

7. Collected guanidine soluble fraction and dialyzed against PBS in 10K MWCO Slide-A-Lyzer overnight against 5 L PBS (3 slide-a-lyzers with one 5L and 5 slide-a-lyzers in another 5L) to remove guanidine.

8. Changed PBS and dialyzed for additional 9 hours at 4°C with stirring.

9. Collected the dialysate and stored at 4°C.

10. Centrifuged at 16,500 RPM on Hermle Z-252M, at 4°C for 5min

11. Removed PBS soluble fraction for DEAE-Sepharose chromatography.

DEAE-Sepharose Chromatography

1. Increased the NaCl concentration of 500µl of PBS soluble guanidine extract to 300mM NaCl (Assumed PBS soluble fractions were already at ~150mM NaCl, so added 15µl 5M NaCl stock to each 500µl sample).

2. Equilibrated ~1ml of packed DEAE-Sepharose (previously washed with 1M NaCl/PB pH 7.2) into 300mM NaCl/PB pH 7.2 (Note: To make 300mM NaCl/PB pH7.2 - added 3ml of 5M NaCl stock to 100ml PBS).

3. Added 200µl of 1:1 slurry of resin to 515µL of GuHCl extracts (both at 300mM NaCl).

4. Nutated at ambient temperature for ~ one hour.

5. Centrifuged gently to pellet resin.

6. Removed "unbound" sample and stored at -20°C.

7. Washed resin 5 times with ~1.5ml of 300mM NaCl/PBS pH7.2.

8. After last wash, removed all extra buffer using a 100µl Hamilton syringe.

9. Eluted at ambient temperature with three 100µl volumes of 1M NaCl/PB pH 7.2 and stored at -20°C.

SDS -PAGE:

5-20% gradient gels for analysis of PBS soluble Guanidine HCl extracts and DEAE-Sephadex chromatography.

- 5 1. Gel#1: GuHCl extracts/ PBS soluble fractions- Toluidine blue and then Coomassie blue stained.
2. Gel#2: DEAE-Sephadex Eluant Fraction#1 - Toluidine Blue stained then Coomassie Blue stained.

10 Quantification of Collagen Crosslinks by HPLC:

Prepared 100-200 μ l 1x solution in 1% heptafluorobutyric acid (HFBA).

Injected 50 μ l on C18 HPLC column equilibrated with mobile phase.

Spectrofluorometer was set for excitation at 295nm and emission at 395nm.

15 Calculated the integrated fluorescence of Internal-Pyridinoline (Int-Pyd) per 1 μ l of 1x solution of Int-Pyd.

Results:

20 The HPLC results are shown in Figures 2A-D. The major peak represents the Internal-Pyridinoline (Int-Pyd) peak. Irradiation in an aqueous environment (PBS) produced pronounced decreases in the smaller peaks (Figure 2A). Reduction of the water content by the addition of a non-aqueous solvent (PPG 400) produced a nearly superimposable curve (Figure 2B). DMSO was less effective (Figure 2C), while DMSO plus a mixture of stabilizers (Figure 2D) was more effective at preserving the major peak although some minor peaks increased somewhat. The area under the

25 pyd peak for each sample was calculated as shown in the table below. These results confirm the above conclusions and show that the amino acid crosslinks (pyd) found in mature collagen are effectively conserved in the samples containing PPG and DMSO with a scavenger mixture. Gel analysis is shown in Figure 2E and reflects the major conclusions from the HPLC analysis, with significant loss of bands seen in PBS and retention of the major bands in the presence of non-

30 aqueous solvents.

Sample	Area of Pyd Peak
PBS/ 0kGy	94346
PBS/ 25kGy	60324
DMSO/ 0kGy	87880
DMSO/ 25kGy	49030
DMSO/ SM/ 0kGy	75515
DMSO/ SM/ 25kGy	88714
PPG/ 0kGy	99002
PPG/ 25kGy	110182

Example 3

5 In this experiment, frozen porcine AV heart valves soaked in various solvents were gamma irradiated to a total dose of 30 kGy at 1.584 kGy/hr at -20°C.

Materials:

- 10 1. Porcine heart valve cusps were obtained and stored at -80°C in a cryopreservative solution (Containing Fetal calf serum, Penicillin-Streptomycin, M199 media, and approximately 20% DMSO).
2. Dulbecco's Phosphate Buffered Saline. Gibco BRL: cat#14190-144, lot#1095027
3. 2 ml screw cap vials. VWR: cat# 20170-221, lot #0359
4. 2 ml glass vials. Wheaton: cat# 223583, lot#370000-01
- 15 13 mm stoppers. Stelmi: 6720GC, lot#G006/5511
- DMSO. JT Baker: cat# 9224-01, lot# H40630
- Sodium ascorbate. Aldrich: cat# 26,855-0, lot 10801HU; prepared as a 2M stock in Nerl water.
8. Fetal calf serum
9. Penicillin-Streptomycin
- 20 10. M199 media
11. DMSO

Methods:**Preparation of Solutions****Freeze Medium:**

- 5 Fetal calf serum (FCS) (10%) = 50 ml
Penicillin-Streptomycin = 2.5 ml
M199 = QS 500 ml

2M DMSO

- 10 DMSO = 15.62 g
Freeze Medium = QS 100 ml

3M DMSO

- DMSO = 23.44 g
Freeze Medium = QS 100 ml

15 Preparation of Tissue

Placed dissected heart valves (with a small amount of conduit/muscle attached) into glass freezing tubes (label with pencil).

Added 2 ml of freeze medium.

At 21°C, added 1 ml 2M DMSO solution.

- 20 At 5 minutes, added 1 ml 2M DMSO solution.

At 30 minutes, added 4 ml 3M DMSO solution.

At 45 minutes and 4°C, placed freezing tubes on ice.

At 50 minutes and -7.2 °C, seeded bath, which is an alcohol filled tank inside the cryopreservation machine and is used to lower the temperature quickly.

- 25 At 55 minutes and -7.2°C, nucleated. Nucleation is a processing step that allows the tissue to freeze evenly and quickly without much ice formation. This is done by placing a steel probe in a liquid nitrogen canister, touching the probe to the outside of the freezing tube at the surface of the solution, waiting for ice formation, shaking the tube and placing the tube in the bath.

- At 70 minutes, cooled to -40°C at 1°C/minute. Removed from bath and placed in canister of liquid N₂, and stored in cryogenic storage vessel.

30

Procedure for Irradiation of Heart Valves:

1. Thawed AV heart valve cusps on wet ice.

2. Pooled cusps into 50 ml tubes.

3. Washed cusps with ~50ml dPBS at 4°C while nutating. Changed PBS 5 times over the course of 5 hrs.

4. Transferred cusps into 2 ml screw cap tubes (2 cusps/tube).

5. Added 1.0 ml of the following to two of each of two tubes: dPBS, 50% DMSO and 50% DMSO with 200 mM sodium ascorbate (2M sodium ascorbate stock was diluted as follows: 400µl (2M) + 1.6 ml water + 2ml 100% DMSO).

6. Incubated tubes at 4°C with nutating for ~46 hours.

7. Transferred solutions and cusps to glass 2 ml vials, stoppered and capped.

8. All vials were frozen on dry ice.

9. Frozen samples were then irradiated at -20°C at a rate of 1.584 kGy/hr to a total dose of 30 kGy.

Results:

The results of the HPLC analysis are shown in Figures 3A-3D. Irradiation in an aqueous environment (PBS) produced decreases in the smaller peaks (Figure 3A). Reduction of the water content by the addition of a non-aqueous solvent (20% DMSO) reproduced these peaks more faithfully (Figure 3B). Increasing the DMSO concentration to 50% was slightly more effective (Figure 3C), while DMSO plus a mixture of stabilizers (Figure 3D) was very effective at preserving both the major and minor peaks (the additional new peaks are due to the stabilizers themselves). Gel analysis is shown in Figure 3E and reflects the major conclusions from the HPLC analysis, with significant loss of bands seen in PBS and retention of the major bands in the presence of non-aqueous solvents with and without stabilizers.

Example 4

In this experiment, frozen porcine AV heart valves soaked in various solvents were gamma irradiated to a total dose of 45 kGy at approximately 6 kGy/hr at -70°C.

Materials:

Porcine heart valve cusps were obtained and stored at -80°C in a cryopreservative solution (Same solution as that in Example 3).

Dulbecco's Phosphate Buffered Saline (dPBS). Gibco BRL: cat#14190-144, lot 1095027

30 3. 2 ml screw cap vials. VWR: cat# 20170-221, lot #0359

4. 2 ml glass vials. Wheaton: cat# 223583, lot#370000-01

5. 13 mm stoppers. Stelmi: 6720GC, lot#G006/5511

6. DMSO. JT Baker: cat# 9224-01, lot# H40630

7. Sodium ascorbate. Aldrich: cat# 26,855-0, lot 10801HU; prepared as a 2M stock in Nerl water.

8. Polypropylene glycol 400 (PPG400). Fluka: cat#81350, lot#386716/1

Methods:

5 Cryopreservative Procedure is the same as that shown in Example 3.

1. Thawed AV heart valve cusps on wet ice. Dissected out cusps and washed the pooled cusps 6 times with cold PBS.

2. Dried each cusp and transferred cusps into 2 ml screw cap tubes (2 cusps/tube).

10 3. Added 1.2 ml of the following to two of each of two tubes: dPBS, dPBS with 200 mM sodium ascorbate, PPG400, PPG400 for rehydration, 50% DMSO and 50% DMSO with 200 mM sodium ascorbate (2M sodium ascorbate stock was diluted as follows: 400 μ l (2M) + 1.6 ml water + 2ml 100% DMSO).

4. Incubated tubes at 4°C with nutating for ~46 hours.

15 5. Replaced all solutions with fresh solutions (with the following exception: for one PPG400 set, PPG400 was removed, the cusp washed with PBS+200 mM ascorbate, which was then removed and replaced with fresh PBS+200 mM ascorbate).

6. Incubated tubes at 4°C with nutating for ~46 hours.

7. Changed the solution on the PPG400 dehyd./PBS+ascorbate rehydration cusps prepared in step 5.

20 8. Incubated tubes at 4°C with nutating for ~6 hours.

9. Transferred solutions and cusps to glass 2 ml vials, stoppered and capped.

10. All vials were frozen on dry ice.

25 11. 5Frozen samples were then irradiated at -70°C at a rate of 6 kGy/hr to a total dose of 45 kGy.

Results:

30 The results of the HPLC analysis are shown in Figures 4A-4F. Irradiation in an aqueous environment (PBS) resulted in changes in the minor peaks and a right shift in the major peak. The inclusion of various non-aqueous solvents, reduction in residual water, and the addition of stabilizers produced profiles that more closely matched those of the corresponding controls. The gel analysis is shown in Figures 4G-4H and shows a significant loss of bands in PBS, while the other groups demonstrated a significant retention of these lost bands.

When comparing the results from Example 4 to the results from Examples 1, 2, and 3, it becomes apparent that lowering the temperature for the gamma irradiation usually results in a decrease in the amount of modification or damage to the collagen crosslinks. One illustration of this temperature dependence is the sample containing 50% DMSO and ascorbate, in which the additional peaks are markedly decreased as the temperature is lowered from -20°C to -80°C. It is also clear that reducing residual water content by replacing it with a non-aqueous solvent results in less damage or modification, as does adding the stabilizers shown.

Example 5 [091701tg058]

In this experiment, the protective effect of the absence or presence of a stabilizer cocktail on frozen porcine ACL samples, which were gamma irradiated to a total dose of 45 kGy at approximately 6 kGy/hr at -80°C, was evaluated.

Materials:

Porcine ACL samples were obtained and placed in 15% DMSO or 15% DMSO containing 100 mM ascorbate, 100 mM deferoxamine, and 22 mM ergothioneine and incubated for 1 hour at 37°C with agitation and then at 4°C for 24 hours.

The ACL samples were quick frozen in ethanol, dry-ice bath and then stored at -80°C until irradiation

Methods:

ACL samples were sent to the irradiator on dry ice.

Gamma irradiation was performed at NIST at 5.18 kGy/hour to a total dose of 45 kGy at an average temperature of -75°C. The 0kGy controls were maintained on dry ice.

Irradiated samples were as follows:

- 4 M Guanidine-0.5 M sodium acetate, pH 5.8 extraction and SDS-PAGE;
- Pepsinolysis of guanidine residue and SDS-PAGE;
- CNBr digest of pepsin residue and SDS-PAGE;
- SDS-PAGE of CNBr digest residue; and
- Hydrolysis and evaluation of pyridinoline crosslinks by HPLC.

Results:

As illustrated in Figure 5A, fewer proteins overall were extracted by guanidine/acetate following irradiation to 45 kGy, and of those that were extracted, there was significantly less protein

in the 45 kGy sample than the control sample subjected to 0 kGy of irradiation. Additionally, also in Figure 5A, there are a series of bands around 205 kD that are absent from the 5 kGy sample. The top two of the four bands were detected, however, in the 45 kGy sample with the cocktail. There are three darker staining bands that run just above the 119 kD marker, the top band of which appears to be sensitive to gamma irradiation. Additionally, there are a series of bands around 205 kD that are absent from the 45kGy sample.

Also, as illustrated in Figure 5A, the SDS-PAGE analysis of the pepsin-solubilized component of the guanidine/acetate residue indicates that more material was extracted by pepsinolysis following 45 kGy of gamma irradiation compared to the 0 kGy controls. There also appeared to be a significant difference between the 0 and 45 kGy samples in the region of 52 to 119 kD. Additionally, there is evidence of increased smearing and higher molecular weight material that does not enter the gel in the 45 kGy sample lanes. There also does not seem to be a gross difference between the 45 kGy samples with or without the cocktail.

Further, as illustrated in Figure 5A, no differences appear among the samples following CNBr cleavage of the residue left after pepsin digestion. As illustrated in Figures 5B-5E, HPLC analysis of the Pyridinoline crosslinks indicates that there is about a 20% loss in crosslink of the 45 kGy samples compared to the 0kGy sample. The peak profiles of the samples containing cocktail are broader and there appears to be a loss of symmetry. The cocktail or ratio of tissue to HCl during may also affect the hydrolysis.

Pretreatment of the ACL tissue with the AED stabilizer cocktail provided minimal protection to radiation-induced damage. SDS-PAGE of the guanidine extracted material indicated that several higher molecular weight proteins are sensitive to gamma irradiation and therefore might serve as markers for later evaluation.

Example 6

In this experiment, the effect of gamma irradiation on frozen porcine ACL samples soaked in the absence or presence of a stabilizer was evaluated

Materials:

Porcine ACL samples with the following stabilizers were prepared:

- 200 mM sodium ascorbate (Spectrum S1329 QP 0839) in water;
- 100 mM thiourea (Sigma T8656, 11K01781) in water;
- 200 mM L-histidine (Sigma H8776, 69H1251) in PBS;

500 mM D(+)-trehalose (Sigma T9531, 61K7026) in water;

5 mg/mL ergothionine (Sigma E7521, 21K1683) in water;

0.01 M poly-Lysine (Sigma, MW 461);

PPG for 1 hour at 37°C, then removed and soaked in a PPG cocktail of 100 µM trolox C
5 (Aldrich 23,881-3, 02507TS, 53188-07-01) in DPBS, 100 mM lipoic acid (Calbiochem 437692,
B34484), 100 mM coumeric acid (Sigma) in ethyl alcohol and 100 mM n-propyl gallate (Sigma
P3130, 60K0877) in ethyl alcohol; and
No stabilizers added (water only).

10 **Methods:**

ACL samples were prepared by cutting each sample in half in the longitudinal direction;

Porcine ACL samples were obtained and placed in one of the stabilizers for 1 hour in a
shaking incubator at 37°C;

Next, the samples were dehydrated for 1 hour at 37°C in PPG 400;

15 The samples were then placed at 4°C with the stabilizer previously used for an additional 1
hour, and then fresh stabilizers were added and soaking occurred for 3 days at 4°C. Then the
samples were decanted and freeze dried. Fresh stabilizers were also added prior to freeze drying.

ACL samples were freeze dried, then gamma irradiation was performed at NIST with 0 and
45 kGy of gamma irradiation at 1.677 kGy/hr.

20 Irradiated samples were as follows:

Control (ACL) in water;

ACL + 200 mM sodium ascorbate, pH 7.63;

ACL + 100 mM thiourea, pH 6.63;

ACL + 200 mM L-histidine, pH 8.24;

25 ACL + 500 mM trehalose, pH 5.24;

ACL + 5 mg/mL ergothionine, pH 6.0;

ACL + 0.01 M poly-Lysine, pH 5.59; and

ACL dehydrated + PPG cocktail (100 µM trolox C, 100 mM lipoic acid, 100 mM coumeric
acid and 100 mM n-propyl gallate), pH 5.24.

30 Guanidine HCL extraction was done with 4 M GuHCl in 0.5 NaOAC pH 5.8 and 5 mM
EDTA, 10 mM NEM, 5 mM Benzamidine and 1 mM PMSF to a final concentration of 100 mg/ml of

wet tissue weight/ml of extraction buffer. The samples were incubated at 4°C on a nutator for 2 days.

Pepsin digestion was done by first centrifuging these extracts, then transferring the remaining pellets into a 2 ml tube. The pellets were then washed 3 times with 0.5 M HOAc. Pepsin
5 was added at 1:10 of enzyme:tissue in 0.5 M HOAc and incubated at 4°C overnight.

For pepsin-digested supernatant, NaCl from 5 M stock solution was added to a final concentration of 1M. The supernatants were centrifuged and collagen gel pellets were resuspended in 1 ml of 0.5 M HOAc with gentle mixing at 4°C.

Performed DEAE chromatography on dialysates of Guanidine extracts of samples. Eluants
10 from the DEAE column were subjected to SDS-PAGE and visualized by staining with Toluidine Blue.

A BCA assay was performed on the dialysates of the PPG + cocktail guanidine extracted samples to determine the total protein concentration in the samples.

Extracted PPG + cocktail treated samples using Urea/SDS/β-Me extraction buffer. The
15 extractible noncollagenous proteins were analyzed by SDS-PAGE under reducing conditions.

Results:

The ACL samples were rehydrated with water for a few hours at room temperature, where a measured length of each ligament was cut and weighed. The weights of the cut pieces is as
20 follows:

Sample	0 kGy (mg)	45 kGy (mg)
No stabilizer	134.5	150.45
sodium ascorbate	171.95	148
thiourea	288.6	183.06
L-histidine	229.3	226.54
D(+)-trehalose	260	197.5
ergothionine	165.14	132.68
poly-Lysine	289.34	164.88
PPG cocktail	114.5	83.93

From the SDS-PAGE of pepsin digest, the cocktail treated ACL showed the best recovery compared to the other stabilizers. The HMW bands, as illustrated in Figure 6A, were protected after irradiation in the presence of the cocktail mix.

For the purified pepsin-digested collagen, the PPG dehydration and rehydration with cocktail showed the best recovery by SDS-PAGE. The yield, as illustrated in Figures 6B, 6C and 6D was about 88% for the cocktails comparing to 32% for the control. However, some of the HMW bands were destroyed by irradiation even in the presence of the cocktails. These other stabilizers were not effective in protecting the collagen in this experiment.

The turbidity of the collagen appeared to be lower in the presence of the cocktail with a lower rate of fibril formation compared to the un-irradiated collagen.

SDS-PAGE of the guanidine extracts, as illustrated in Figure 6E indicate severe damage to the extractable proteins following irradiation to 45 kGy as compared to the corresponding 0 kGy control. The addition of the various stabilizers gave variable results. The 0 kGy controls differed from one another which either reflects the efficiency of their extraction in the presence of the various stabilizers or is an artefact of the dialysis. Trehalose and poy-lysine provided the least protection. Ascorbate and histidine provided the most promising results for protecting a broad spectrum of the proteins, while ergothionine showed good protection of proteins in the lower 2/3 of the gel. The cocktail provided protection to the proteins in the region above the 119 kD marker. However, the very high molecular weight proteins were not well preserved by any of the stabilizers.

Using DEAE chromatography, as illustrated in Figure 6F, the proteoglycan profile appeared varied and inconsistent from sample to sample and from control to control. It is unclear whether the stabilizers were affected. It is clear, however, that there is a high molecular weight proteoglycan (>200 kD) that was purified in several of the samples. Most of the samples had a band that migrated similar to that of the recombinant human decorin. However, it is not clear whether it is porcine decorin.

Using BCA and SDS-PAGE on the PPG + Cocktail sample, guanidine extracts were evaluated based on SDS-PAGE of equal protein load. The protein concentrations were as follows:

fdL/PPG + C/0	1270 ng/ μ L
fdL/PPG + C/45	249 ng/ μ L

Although there appears to be significantly less protein in the 45 kGy sample based on concentration alone, there appears to be a similar amount of total protein when the volume was taken into consideration where the 45 kGy sample appears diluted. Additionally, the SDS-PAGE

analysis shows loss of specific protein bands with other bands appearing to be less sensitive to radiation. Densitometry was performed on two different protein bands, as follows:

	background	4.52		
	0 kGy	50.26		
5	45 kGy	26.87	percent of 0 kGy:	53.5%
	background	2.33		
	0 kGy	70.26		
	45 kGy	50.54	percent of 0 kGy:	71.9%

10 It is appears that the different recoveries observed are due to differences in sensitivity to radiation or due to a difference in extraction ability. For example, the loss observed in the 45 kGy sample might be due to a differential loss (i.e. - damage) of the proteins or might be due to radiation-induced cross linking that results in a different ability of various proteins to be extracted.

Using Urea/SDS/ β -Me extraction the initial difference in guanidine extraction of the PPG + cocktail samples can be observed. It appears that the PPG + cocktail treatment resulted in significant protection of the extractible proteins at 45 kGy of gamma irradiation compared to the 45 kGy sample without treatment. However, it is noted that the PPG + cocktail sample did not rehydrate, but the lack of rehydration appears to be irradiation independent and therefore caused by some component or combination of components in the treatment, which was investigated in
20 Example 7, as follows.

Example 7

In this experiment, the protective effect of the PPG + cocktail treatment of Example 6 was observed to determine whether the ACL sample was adversely affected due to the lack of
25 rehydration.

Materials:

30 α -Lipoic Acid (Calbiochem #437692, lot B34484);
Trolox C (Aldrich #23,881-3, lot 02507TS);
n-Propyl Gallate (Sigma #P-3130, lot 60K0877);
p-Coumaric Acid (Sigma #C-9008, lot 49H3600);
Polypropylene Glycol P400 (Fluka #81350, lot 386716/1);
5 mL tubes;

left ACL (received from RadTag Technologies);

Ethyl Alcohol (Burdick & Jackson, #AH090-4, lot BX488)

Methods:

5 The ACL samples was sectioned and dehydrated in PPG for 2 hours @ 37°C with shaking.

Components of the stabilizer cocktail were made individually by making the stocks, then diluting them with 40% ethanol (which alone does not prevent rehydration of the tissue), where the individual stabilizers/controls were as follows:

2mM Trolox C in PBS (diluted 1:20 in 40% ethanol, final of 100 μ M)

10 1 M propyl gallate dissolved in ethanol (diluted 1:10, final of 100 mM in 40% ethanol)

0.5 M coumaric acid in ethanol (diluted 1:5, final 100 mM in 40% ethanol)

0.5 M lipoic acid initially dissolved in NaOH and then the volume and pH were adjusted to neutral (diluted 1:5 in 40% ethanol)

40% ethanol

15 water

Following a 2 hour incubation in PPG, the tissue was removed and blotted to remove excess PPG and 2 mL of the individual stabilizers/controls (a-f) were added.

Samples were then placed on a shaker at 4°C and allowed to rehydrate overnight.

20

Results:

The ACL tissue samples were rehydrated to a normal appearance except the sample treated with PPG and coumaric acid. The coumaric acid was then tested without the PPG, but still
25 did not result in a normal process by rehydration and instead led to adverse properties of the ACL tissue sample which appeared dehydrated and sticky to the touch.

Example 8

In this experiment, the protective effect of a cryopreservative on a gamma irradiated
30 regulated or quick freeze dried ACL at -80°C was evaluated.

Materials:

Edmonton cryopreservative media (M199, 10%FCS, Penicillin-Streptomycin, 2 M DMSO

Modified VS55 cryoprotectant (100 mM trehalose, 15 mM KH_2PO_4 , 42 mM K_2HPO_4 , 15 mM KCl, 10 mM NaHCO_3 , 150 mM mannitol, 24.2% DMSO, 16.8% 1,2-propanediol, 14% formamide).

5 See US Patent 6,194,137 B1.

200 mM sodium ascorbate

Methods:

10 ACL samples were submerged in either the Edmonton or VS 55 media.

Samples were frozen by reducing the temperature 1°C per minute to -40°C in the freeze dryer and then placing the samples at -80°C (regulated freeze) or freezing in a dry ice-ethanol bath (quick freeze).

Irradiations were performed at NIST on dry ice using 5.2 kGy/h to a total dose of 50 kGy.

15 The following analyses were performed:

Gnd-HCL extraction and SDS-PAGE;

Urea/SDS/ β -Me extraction and SDS-PAGE;

Collagenase digestion of Gnd-HCL residue and SDS-PAGE;

Collagen purification and SDS-PAGE; and

20 DEAE chromatography and SDS-PAGE.

Results:

25 Purification of proteoglycans by DEAE chromatography appeared to show that the cryopreservative treatment influenced the ability of the proteoglycans to be purified, as illustrated in Figure 7A. Also as illustrated in Figure 7A, all samples submerged in Edmonton CP had a similar profile, but varied in intensity. On the other hand, as further illustrated in Figure 7A, treatment with VS55 gave poor recovery of proteoglycans under the quick freezing regimen, whereas the regulated freeze resulted in good recovery except in the sample containing ascorbate.

30 A table of the percent recovery of the major band observed by SDS-PAGE, comparing the irradiated sample to its corresponding control for the guanidine extracts, is given below. For the samples treated with CP, those samples in which 200 mM ascorbate was added, had a lower

percent recovery than the sample without ascorbate. And, the quick freeze gave better recovery than the regulated freeze. Whereas, with the mVS55 treated samples the regulated freeze had better recovery based on the densitometry of single band. However, by visual examination, the overall total protein extracted from the regulated freeze appeared to be less than that extracted from the quick freeze. Additionally, the exaggerated percent recoveries (>100%) are likely an artefact of smearing and the absence of some of the higher molecular weight proteins. However, the mVS55 does seem to give better recovery of these high molecular weight proteins (around 205 kDa) in the irradiated samples than other irradiated samples without mVS55.

The gels of the Urea/SDS/ β -Me extractible proteins appear to be consistent with the results observed with the guanidine extraction, Figure 7B. Densitometry was not performed on these samples as the smearing observed in the irradiated samples leads to inaccurate readings. To that end, the obvious presence of the smearing indicates damage to tissue proteins following irradiation.

Major Band							
Edmonton CP				Modified VS55			
	Dens.	Blank Sub.	%Recovery		Dens.	Blank Sub.	%Recovery
Quick Freeze				Quick Freeze			
Blank	27.71	0		Blank	45.91	0	
0 kGy	137.3	109.59	100	0 kGy	161.68	115.77	100
50 kGy	138.75	111.04	101	50 kGy	161.52	115.61	100
Asc. 0 kGy	137.05	109.34	100	Asc. 0 kGy	166.56	120.65	100
Asc. 45 kGy	122.75	95.04	87	Asc. 45 kGy	151.4	105.49	87
Regulated Freeze				Regulated Freeze			
Blank	27.71	0		Blank	40.07	0	
0 kGy	135.98	108.27	100	0 kGy	126.39	86.32	100
50 kGy	104.54	76.83	71	50 kGy	139.27	99.2	115
Asc. 0 kGy	137.14	109.43	100	Asc. 0 kGy	128.19	88.12	100
Asc. 45 kGy	95.79	68.08	62	Asc. 45 kGy	152.55	112.48	128

From the SDS-PAGE, purified pepsin-digested collagen from the VS55 cryopreservatives without ascorbate showed the best recovery, as illustrated in Figure 7C and in the following table:

Regulated Freezing				Quick Freeze			
Density of a chain Collagen			%Recovery	Density of a chain Collagen			%Recovery
Blk	15.01	0		Blk	50.99	0	
VS55/0kGy	46.39	31.38	100	VS55/0kGy	112.45	61.46	100
VS55/50kGy	51.72	36.71	117	VS55/50kGy	100.75	49.76	81
VS/A/0kGy	53.53	38.52	100	VS/A/0kGy	117.61	66.62	100
VS/A/50kGy	42.79	27.78	72	VS/A/50kGy	88.7	37.71	57
CP/0kGy	58.7	43.76	100	CP/0kGy	112.36	61.37	100
CP/50kGy	43.92	28.91	66	CP/50kGy	86.21	35.22	57
CP/A/0kGy	80.98	65.97	100	CP/A/0kGy	122.36	71.37	100
CP/A/50kGy	56.02	41.01	62	CP/A/50kGy	87.42	36.43	51

- 5 Turbidity results for pepsin-digested collagen from ACL in VS55 cryopreservative did not correlate well with the SDS-PAGE data for regulated freeze and quick freeze ACL samples. The collagen from irradiated ACL in VS55 did not form fibril as expected, probably due to the presence of degraded proteins and loss of high molecular weight protein bands after irradiation (which interfere with the assay). For other cryopreservatives turbidity results correlated quite well with the
- 10 SDS-PAGE results for quick freeze and regulated freeze ACL samples.

Example 9

- This experiment was to determine whether ethanol dehydration or drying ACL will help to remove water and whether a rehydration process would deliver cocktail of antioxidants inside ACL
- 15 tissue to protect it from γ -irradiation at 4°C with 50 kGy.

Materials:

- 20 1. 2mM trolox C [Aldrich 23,881-3, 02507TS, 53188-07-01] in DPBS
2. 0.5M lipoic acid [Calbiochem 437692, B34484] in 100% ethanol
3. 0.5 M coumeric acid [Sigma C4400] in ethyl alcohol
4. 1M n-propyl gallate [Sigma P3130, 60K0877] in ethyl alcohol

5. 10 mg/ml Ergothionine [Sigma E7521, 21K1683] in water.

Samples were prepared by cutting ACL in small chunk and used for irradiation as following:

1. Control (ACL)
2. Cocktails (100 μ M trolox, 100mM coumeric acid, 100mM lipoic acid, 100mM n-propyl gallate)
3. Cocktails + 5mg/ml ergothionine.

Methods:

1. Six pieces of ACL were dried overnight to remove water.
2. Another six pieces were soaked in 25% ethanol for 2hr at room temperature (rt), then 50% ethanol for 1 hr at rt and 75% ethanol for overnight at rt.
3. Soaked another 6 pieces of ACL in 100% ethanol for 6hr at rt and these ACLs were incubated with either cocktails or modified cocktails solutions for 2hr with shaking in a shaking incubator at 37°C. After 2hr incubation, these ACL tubes were decanted and fresh solution of anti-oxidants were added to each ACL containing tubes and incubated for overnight at 4°C.
4. All the tubes were freeze-dried for 2 days.
5. The samples were irradiated with 0 and 50 kGy at 1.656 kGy/hr at NIST.
6. The ligaments were rehydrated with water for a few hours at rt.
7. Washed extensively with DPBS.
8. For ethanol dehydration ACL samples, rehydration was repeated by washing with the gradient of 75%, 50%, and 25% ethanol. Then washed with DPBS extensively.
9. Cut a small piece from each sample and weighed all of the cut pieces.
 - a) ETOH 0kGy = 25.12 mg
45k = 10.5 mg
 - b) ETOH/Cocktails 0kGy = 25.6 mg
45kGy = 32.4 mg
 - c) ETOH/modified 0kGy = 30.45mg
45kGy = 30.3 mg
 - d) FD 0kGy = 30.1mg
45 kGy = 16.3mg
 - e) FD/cocktails 0kGy = 33.3 mg.
45 kGy = 31.51 mg
 - f) FD/modified 0 kGy = 30 mg

45 kGy = 26.5 mg

10. ACLs were digested with pepsin and collagen was purified by salt precipitation.
11. Collagen gel pellets were resuspended in 1ml of 0.5 N HOAc with gently mixing at 4°C.
12. The pepsin-digested collagens for control and cocktails treated ACL were dialyzed against 5mM HOAc for overnight.
13. Determined the OD 218nm for each collagen preparation.
14. Turbidity assay was performed for these collagens.

Results:

The purified pepsin-digested collagen for ethanol dehydration of ACL with cocktails without ergothionine, as illustrated in Figure 8, showed the best recovery compared with cocktails with ergothionine by SDS-PAGE. The yield was 88% for the cocktails with ethanol dehydration comparing to 83% for freeze-dried dehydration. The cocktails of scavengers and ergothionine was a little less effective than that of cocktails alone.

Ethanol dehydration seemed to give a little bit better recovery than the freeze-dried dehydration process for ACL.

Example 10

This experiment was to determine whether high salt, low salt, neutral pH and low pH treated ACL will help to deliver stabilizers into ACL tissue to protect it from γ -irradiation at -80°C with 50 kGy.

Method

1. Prepared stock solution 2M sodium ascorbate (Spectrum S1349, Lot#QP0839) in water. Samples were prepared with the following:

- a) DPBS
- b) DPBS/200mM sodium ascorbate
- c) 0.5N HOAc
- d) 0.5N HOAc/200mM sodium ascorbate
- e) 20mM sodium phosphate pH 7.6
- f) 20 mM sodium phosphate pH 7.6/200mM sodium ascorbate

- g) 20mM sodium phosphate pH 7.6/1M NaCl
- h) 20mM sodium phosphate pH 7.6/1M NaCl/200mM sodium ascorbate.
- 2. These samples were irradiated with 0 and 50 kGy at 1.53 kGy/hr at NIST.
- 3. A small piece was cut from each sample and weighed as follows:

5

a)	DPBS	0kGy = 32.7 mg 45k = 10.7mg
b)	DPBS/Asc	0kGy = 25.12 mg 45kGy = 26 mg
c)	0.5N HOAc	0kGy = 37.3mg 45kGy = 35.5 mg
d)	0.5N HOAc/Asc	0kGy = 21.2 mg 45 kGy = 41.4mg
e)	20mM PO ₄	0kGy = 22.87 mg 45k Gy = 36.3mg
f)	20mM PO ₄ /Asc	0 kGy = 24mg 45 kGy = 18.04 mg
g)	20mM PO ₄ /NaCl	0kGy = 21.41 mg 45kGy = 21.2 mg
h)	20mM PO ₄ /NaCl/Asc	0kGy = 33.76 mg 45kGy = 21 mg

10

15

20

- 4. ACL were digested with pepsin and collagen purified by precipitating with salt.

Results:

25

The purified pepsin-digested collagen from ACL irradiated at -80°C with 0.5N HOAc pH 3.4, as illustrated in Figs. 9A and 9B, showed the best recovery compared with 20mM sodium phosphate pH 7.6 with or without 1M NaCl or PBS alone by SDS-PAGE. The yield at 50kGy was 83% with ascorbate and 73% without ascorbate. ACL irradiated with 20mM sodium phosphate pH 7.6 without salt yielded good recovery at 75% and 60% in the presence and absence of ascorbate, respectively. ACL irradiated with high salt showed the worst recovery only 40% with or without ascorbate.

30

The turbidity assay appeared to have the collagen isolated from the ACL samples. Also, the washing of the collagen gel pellet after salt precipitation seemed to help. Collagen isolated from

ACL irradiated with 0.5N HOAc showed the best results, which correlated with SDS PAGE results. However, the turbidity curves of collagens from ACL irradiated in the presence of ascorbate did not quite correlate with SDS PAGE results, which showed better recovery than that of ACL irradiated under conditions without ascorbate, which may be caused because the ascorbate may not have
5 been completely removed from the ACL sample.

Also, it appeared that the ACL sample soaking with 0.5N HOAc caused the tissue to swell and become larger than its original size. After washing with DPBS, however, the tissue appeared to change back to its original size.

10 *Example 11*

This experiment was to determine whether alcohols can protect ACL tissue samples from γ -irradiation at -80°C with 50 kGy.

Methods:

1. ACL samples were prepared by preparing small portions of ACL sample with the
15 following:
 - a) ethanol
 - b) 1,2-propanediol
 - c) 2,3-butanediol
2. These samples were then incubated with different alcohols for 2hr in a shaking
20 incubator at 37°C .
3. After 2hr incubation, these ACL tubes were decanted and fresh solutions were added to each ACL containing tubes and incubated overnight at -80°C .
4. These samples were irradiated with 0 and 50 kGy at 1.53 kGy/hr at NIST.
5. These ligaments were washed extensively with DPBS. Small pieces from each
25 sample were cut, then weighed as follows:

a)	DPBS	0kGy = 22.9 mg
		50k = 16.43 mg
b)	DPBS/Asc	0kGy = 47.1 mg
		50kGy = 21.85 mg
30	c) 0.5N HOAc	0kGy = 32.5mg
		50kGy = 30.8 mg
6. ACL were digested with pepsin and collagen purified by precipitating with salt.
7. Turbidity assay was performed for these collagens using at [1mg/ml].

8. Ran 10 μ g of each purified pepsin-digested collages on 4-12% gel and quantified both alpha 1 and alpha 2 chains.

Results:

- 5 The purified pepsin-digested collagen from ACL irradiated at -80°C with ethanol or butanediol showed good recovery, as illustrated in Fig. 10. The yields for 50kGy ACL collagen were 77% and 88% based on the densitometry of alpha 1 and 2 chains of collagen, respectively. Some of the HMW bands (possible β and γ chains of collagen) were completely destroyed by irradiation. Although the recoveries were good, the recovery of collagen isolated from ACL
10 irradiated in the presence of 20mM P04 and ascorbate was still better.

A turbidity assay was performed for the collagen isolated from these ACL samples. Correlation was found between the ACL collagen before and after irradiation. Collagen isolated from ACL irradiated in the presence of alcohol and propanediol could not form fibrils even at higher collagen concentration 0.5 mg/ml comparing to normal used 0.25 mg/ml concentration.

15 Example 12

This experiment was to compare the effects of gamma irradiation on ACL samples that were subjected to three different types of preservation: fresh frozen, freeze dried, or solvent-dried, as these methods of preservation are used by various tissue banks/processors.

Method:

- 20 1. Tissue cross sections were sliced and weighed.
- | | | |
|-------|------------------|----------|
| a. | acl/fresh/-80/0 | 330.0g |
| b. | acl/fresh/-80/45 | 335.9 mg |
| c. | acl/fd/-80/0 | 286.2 mg |
| d. | acl/fd/-80/45 | 272.4 mg |
| 25 e. | acl/ad/-80/0 | 298.9 mg |
| f. | acl/ad/-80/45 | 274.3mg |
2. Fresh ligaments were placed in 2 mL serum vials and frozen in a dry ice-ethanol bath and then stored in a -80°C freezer until irradiation.
3. The freeze-dried ligaments (fd) were placed in 2mL serum vials for freeze drying.
30 The freeze dried tissue was then stored in a -80°C freezer until irradiation.
4. The acetone-dried ligaments were placed in 5 mL conical vials and 5 mL acetone was added. The samples were placed at 4°C on the nutator. The acetone was changed every hour for 4 hours and the 5th acetone wash went overnight. The next morning the

samples were removed from the acetone and blotted dry with a Kimwipe. The dried ligaments were placed in a 2 mL serum vial and the residual acetone was allowed to evaporate in a hood overnight. The acetone-dried ligament appeared to be dehydrated and shriveled. The samples were stored in the -80°C freezer until irradiation.

5 5. All samples were irradiated at NIST to 45 kGy on dry ice (-72°C) at 1.5 kGy/h. The 0 kGy controls traveled and were stored on dry ice at NIST.

6. Rehydrated tissue with 2 mL PBS for 1.5 h at 4°C with shaking on the Nutator.

a. All looked rehydrated except for the acetone-dried tissues that still appeared shriveled and hard to the touch.

10 b. Transferred tissues to conical vials with 20 mL PBS and left overnight at 4°C with shaking on the Nutator.

c. All tissues rehydrated.

7. Extracted noncollagenous protein with Urea/SDS/B-Me extraction buffer. Analyzed samples by SDS-PAGE (4-20% gradient) under reducing conditions.

15 8. Pyd-cross link recovery was determined.

Results:

20 Gamma irradiating ACL's to 45 kGy at low temperature, as illustrated in Figure 11, resulted in better recovery than irradiating freeze-dried ACL's to 45 kGy at 4°C. In addition, the freeze-dried sample irradiated to 45 kGy in this study resulted in a better recovery of noncollagenous proteins than was observed for the freeze-dried 45-kGy-sample irradiated at 4°C.

25 This study indicates that irradiating fresh frozen tissue yields better recovery of the noncollagenous proteins than is observed when the tissue has been dehydrated by freeze drying or solvent drying (acetone) prior to irradiating as indicated by the extensive smearing observed on the gel. Densitometry indicated that the major band seen on the gel was similar in all the 0 kGy controls.

Example 13

30 In this experiment, the effects of gamma irradiation on porcine ACL treated with various stabilizers was investigated.

Preparation of Antioxidant Stock Solutions

The following stock solutions were prepared:

2M sodium ascorbate in water (Spectrum S1349 QP 0839)

2mM trolox C in DPBS(Aldrich 23,881-3, 02507TS, 53188-07-01)

0.5M lipoic acid (Calbiochem 437692, B34484)

0.5M coumaric acid in ethyl alcohol (Sigma)

1M n-propyl gallate in ethyl alcohol (Sigma P3130, 60K0877)

5 0.2M L-histidine in PBS (Sigma H8776, 69H1251)

2M D-(+)-trehalose in water (Sigma T9531, 61K7026)

10 mg/ml ergothionine in water (Sigma E7521, 21K1683)

0.04M poly-lysine (Sigma, MW=461)

1M thiourea (Sigma T8656, 11K01781)

10 Preparation of Ligament Samples

Samples were prepared by cutting ACL in half longitudinally. The lengths of each ACL were measured and used for irradiation. The samples were placed in tubes with the following conditions:

1. ACL in water (Control)
- 15 2. ACL + 200mM sodium ascorbate, pH 7.63
3. ACL + 0.1M thiourea, pH 6.64
4. ACL + 200mM histidine, pH 8.24
5. ACL + 500mM trehalose, pH 5.36
6. ACL + 5 mg/ml ergothionine, pH 6.0
- 20 7. ACL + 0.01M poly-lysine, pH 5.59
8. ACL dehydrated + (100 μ M trolox C, 100mM coumaric acid, 100mM lipoic acid, 100mMn-propyl gallate), pH 5.24

Method:

ACL's 1-7 described above were incubated for about 1 to about 2 hours with shaking in a shaking incubator at 37°C. For the dehydration (8), the ACL was incubated with polypropylene glycol 400 (PPG400) for 1 hour at 37°C. The PPG400 treated ACL was incubated with the antioxidant mixture described above for 1 hour at 37°C. After about 2 hours of incubation, the ACL tubes were decanted and fresh solutions of antioxidants, or water for 1, were added to each ACL tube. Following this, the tubes ACL's were incubated for 3 days at 4°C, decanted and freeze-dried.

30 The samples were irradiated with 0 kGy and 45 kGy at 1.677 kGy/hr.

The samples were rehydrated with water for a few hours at room temperature. The length of the ACL's was measured and a small piece was cut from each irradiated ACL. The cut pieces were weighed with the following results:

	Sample Number	0kGy (mg)	45kGy (mg)
	1	134.5	150.45
	2	171.95	148
5	3	288.6	183.06
	4	229.3	226.54
	5	260	197.5
	6	165.14	132.68
	7	289.34	164.88
10	8	114.5	83.93

Guanidine HCl Extraction

The ACL samples were extracted with 4M GuHCl in 0.5M NaOAc, pH 5.8, and 5mM EDTA, 10mM NEM, 5mM benzamidine and 1mM PMSF for a final concentration of 100mg/ml or wet tissue weight/ml of extraction buffer. The samples were incubated on the nutator for 2 days at 4°C.

15 Following incubation, the extracts were centrifuged using a tabletop centrifuge and the pellets were transferred into 2ml tubes and washed 3 times with 2 ml of 0.5M HOAc. Pepsin was added to the pellets at a 1:10 ratio of enzyme to tissue in 0.5N HOAc. The samples were incubated at 4°C overnight and another portion of pepsin was added to each pellet. The samples were incubated on the nutator at 4°C overnight.

20 The samples were centrifuged and washed 3 times with 100mM Tris, pH 8.0, and 20mM CaCl₂. Trypsin was added at a 1:20 ratio of enzyme to wet weight. The samples were mixed and incubated at 37°C overnight.

To the pepsin-digested supernatant, NaCl from 5M stock solution was added to a final concentration of 1M. The supernatants were centrifuged for 15 minutes at 22,000 g in a cold room.
25 Collagen gel pellets were resuspended in 1 ml of 0.5N HOAc with gentle mixing at 4°C.

The pepsin digested collagens for the samples were dialyzed against 5mM HOAc overnight. Determined the OD 218nm for each collagen preparation. A turbidity assay was performed for these collagens using purified pepsin-digested collagen as a control.

Results:

30 From the SDS-PAGE of the pepsin digest, the antioxidant cocktail treated ACL (8) showed the best recovery compared to other antioxidants. The HMW bands were protected after irradiation in the presence of cocktails. The trypsin digest did not provide any conclusive results.

For the purified pepsin-digested collagen, the PPG dehydration and rehydration with scavenger cocktails showed the best recovery by SDS-PAGE. They yield was 88% for the cocktails compared to 32% for the control (1).

Using PPG400 for dehydration of the ACL irreversibly changed the morphology of the ACL,
5 even after rehydration.

Example 14

Method:

Samples of human bone powder were gamma irradiated to a total dose of 20kGy at rates
10 of 0.19, 5 and 30kGy/hr on dry ice. A fourth control sample was not irradiated. After irradiation, the three samples and control were ground to 75-500 μ m particle size and demineralised by decalcifying for 10 hours in 10% formic acid. The ground samples were extracted with guanidine hydrochloride and 5 μ g total protein from each extraction were assayed by RP-HPLC.

As the rate of irradiation increased, there was an increase in the amount of collagen
15 breakdown products.

Example 15

Samples of human bone were gamma irradiated at dose rates of 0.2 or 0.6kGy/hr to total
20 doses of 30, 40 or 50kGy. Following irradiation, the samples were ground and demineralised for 48 hours in 10% formic acid. The osteoinductive activity was measured for each sample using a conventional *in vitro* osteoinductive bioassay. The demineralised bone powder was added to plates containing cell cultures. At 5 and 15 days these cells were examined for the appearance of newly formed bone. The results are summarized in the following table

Total Dose, kGy	Dose Rate, kGy/hr	Osteoinductive Activity
30	0.2	Good
40	0.2	Good
50	0.2	Poor
30	0.6	Poor
40	0.6	Poor
50	0.6	Poor

Example 16

Samples containing 400mg of demineralised human allograft tissue and 0.04ml porcine parvovirus were gamma irradiated to a total dose of 0, 30, 40 or 50kGy. The dose response for viral inactivation of the porcine parvovirus was determined. The results are summarized in the

5 following table:

Sample No.	Total Dose, kGy	Remaining Titer log ₁₀
1	0	5.03
2	30	<1.65
3	40	<1.65
4	50	<1.65

Example 17

In this experiment, type I collagen at -20°C, -80°C or freeze-dried at 4°C were irradiated with gamma radiation to a total dose of 45kGy in the presence of various stabilizers.

10 **Materials:**

The following stock solutions were prepared:

1M thiourea (Sigma T8656) in water;

0.5M coumarin (Sigma CC4261) in ethanol;

0.5M *O*-coumaric acid (Sigma C4400) in ethanol;

15 0.5M curcumin (Sigma C1386) in ethanol;

1M L-cysteine (Sigma C6852) in water;

1M 1,3-dimethyl-2-thiourea (Aldrich 534-13-4) in water;

1M 2-mercaptoethylamine (Sigma M6500) in water; and

1M 1,3-dimethylurea (Sigma D6254) in water.

20 Phosphate buffer solution of 40mM sodium phosphate and 100mM NaCl; pH=7.66.

Methods:

The following samples were prepared to a final volume of 0.5ml:

1mg/ml collagen in 5mM acetic acid (control);

1mg/ml collagen + 0.1M coumaric acid;

1mg/ml collagen + 5mM curcumin;

1mg/ml collagen + 0.1M L-cysteine;

1mg/ml collagen + 0.1M 1,3-dimethyl-2-thiourea;

5 1mg/ml collagen + 0.1M thiourea;

1 mg/ml collagen + 0.1M 2-mercaptoethylamine; and

1mg/ml collagen + 0.1M 1,3-dimethylurea.

The samples were irradiated as follows:

freeze-dried; temperature:4.7°C; dose rate:1.656kGy/hr; total dose:45kGy;

10 temperature:-20.5°C; dose rate:1.537kGy/hr; total does:45kGy; and

temperature:72oC; dose rate:1.530-1.528kGy/hr;45kGy.

Following irradiation, the samples were analyzed by SDS-PAGE. Additionally, the samples were diluted 1:2 with water to give collagen concentrations of 0.5 mg/ml and a turbidity assay was performed to detect collagen fibril formation. Collagen fibril formation was initiated by adding 100μl
15 of phosphate buffer solution. The assay was done in triplicate using a microtiter plate reader at 340nm wavelength.

Results:

Thiourea and 1,3-dimethyl-2-thiourea protected collagen from gamma irradiation at -20°C, with recoveries of 83 and 86 %, respectively. Thiourea and 1,3-dimethyl-2-thiourea also protected
20 the high molecular weight protein bands (possibly gamma chain of collagen). The protective effect of curcumin, cysteine, 2-mercaptoethylamine and 1,2-dimethylurea was less than that observed with thiourea and 1,3-dimethyl-2-thiourea. For the freeze-dried samples irradiated at 4°C, the recoveries for thiourea and 1,3-dimethyl-2-thiourea were 69 and 83%, respectively. Regarding the samples irradiated at -80°C, the recoveries for curcumin, 1,3-dimethyl-2-thiourea and thiourea
25 were 83, 91 and 85%, respectively. Figure 12A-12C illustrate the SDS-PAGE results.

The turbidity assays showed that samples treated with thiourea and 1,3-dimethyl-2-thiourea could form fibrils after irradiation. Additionally, for the samples irradiated at -80°C, 1,2-dimethylthiourea, thiourea, cysteine and 2-mercaptoethylamine could form fibrils after irradiation.

Example 18

In this experiment, the effects of gamma irradiation on liquid and gel collagen samples containing various stabilizers were investigated.

Methods:

5 The following stock solutions were prepared:

- (1) 2M sodium ascorbate (Spectrum S1349 QP 0839) in water;
- (2) 0.25M L-methionine (Sigma M6039 88H11341) in water;
- (3) 1M Gly-Gly (Sigma G3915 127H54052) in water;
- (4) 1M thiourea (Sigma T8656 11k01781) in water; and
- 10 (5) Phosphate buffer solution of 40mM sodium phosphate and 100mM NaCl;
pH=7.66.

The following samples were prepared in duplicate containing either gel or liquid collagen to a final volume of 1ml by adding 0.5ml of phosphate buffer solution with 0.5ml of collagen (1mg/ml) in the presence of the stabilizer(s) indicated:

- 15 (1) Collagen (0.5mg/ml) + no stabilizer (control);
- (2) Collagen (0.5mg/ml) + 50mM ascorbate;
- (3) Collagen (0.5mg/ml) + 50mM ascorbate + 50mM Gly-Gly;
- (4) Collagen (0.5mg/ml) + 25mM thiourea; and
- (5) Collagen (0.5mg/ml) + 25mM methionine.

20 For gel samples, after mixing with the phosphate buffer solution the samples were incubated at room temperature for about 30 minutes. The liquid collagen samples were maintained at 4°C to prevent them from gelling.

The samples were gamma irradiated at about 72°C (frozen on dry ice) at dose rates of about 1.29-1.41kGy to a total dose of 48.73 to 53.38kGy. The irradiated samples were analyzed by
25 SDS-PAGE. Additionally, the samples were diluted 1:2 with water to give collagen concentrations of 0.5 mg/ml and a turbidity assay was performed to detect collagen fibril formation. Collagen fibril formation was initiated by adding 100µl of phosphate buffer solution. The assay was done in triplicate using a microtiter plate reader at 340nm wavelength.

Results:

From SDS-PAGE data, Figure 13, the sample containing the ascorbate/Gly-Gly stabilizer mixture showed the best protective effect for collagen. This stabilizer mixture protected gel collagen more effectively than liquid collagen, with recoveries of 86 and 75%, respectively.

5 Generally, the stabilizers protected gel collagen more effectively than liquid collagen. This may be due the stabilizers being trapped in the gel matrix, thereby being more available to minimize the effects of irradiation.

The turbidity assay results were consistent with the SDS-PAGE analysis. Ascorbate and the ascorbate/Gly-Gly mixture were most effective at protecting gel collagen or liquid collagen.

10

Example 19

In this experiment, the effects of gamma irradiation on samples containing collagen and various stabilizers were investigated.

Methods:

15

The following stock solutions were prepared:

- (1) 2M sodium ascorbate in water;
- (2) 1M Gly-Gly in water;
- (3) 2mM Trolox C in Dulbecco's Phosphate Buffered Saline (DPBS)
- (4) 0.5M lipoic acid; and
- (5) 1M thiourea in water.
- (6) Phosphate buffer solution of 40mM sodium phosphate and 100mM NaCl;

20

pH=7.66.

Samples were prepared in duplicate to a final volume of 0.5ml containing the stabilizer(s) indicated:

25

- (1) Collagen (1mg/ml) in 5mM acetic acid (control);
- (2) Collagen (1mg/ml) + 200mM sodium ascorbate;
- (3) Collagen (1mg/ml) + 200mM sodium ascorbate + 200mM Gly-Gly;
- (4) Collagen (1mg/ml) + 200mM sodium ascorbate + 200mM lipoic acid;
- (5) Collagen (1mg/ml) + 0.4M thiourea; and

(6) Collagen (1mg/ml) + 200 μ M Trolox C

The samples were irradiated as follows:

- (1) Liquid; temperature: 3.7°C; dose rate: 1.67kGy/hr; total dose: 30kGy;
- (2) Liquid; temperature: -20.3°C; dose rate: 1.552kGy/hr; total dose: 30kGy;
- 5 (3) Liquid; temperature: -72.5°C; dose rate: 5.136kGy/hr; total dose: 30kGy;
- (4) Liquid; temperature: 3.7 to 5.4°C; dose rate: 1.67kGy/hr; total dose: 45kGy;
- (5) Liquid; temperature: -18.6 to -20.3°C; dose rate: 1.552kGy/hr; total dose: 45kGy;
- (6) Liquid; temperature: -72.5 to -78°C; dose rate: 5.136kGy/hr; total dose: 45kGy;
- (7) Freeze dried; temperature: 3.7°C; dose rate: 1.67kGy/hr; total dose: 30kGy; and
- 10 (8) Freeze dried; temperature 3.3°C; dose rate: 1.673kGy/hr; total dose: 45kGy.

The samples were analyzed by SDS-PAGE.

Results:

From SDS-PAGE analysis, Figures 14A-14D, the samples containing thiourea irradiated to 30kGy and 45kGy at about -20°C had recoveries of 89 and 86%, respectively. Thiourea also
15 protected the high molecular weight protein bands (possibly gamma chain of collagen). The samples irradiated to 30kGy and 45kGy at about -20°C and containing the ascorbate/Gly-Gly stabilizer mixture had recoveries of 81 and 74%, respectively.

Regarding the samples irradiated at about -80°C, those irradiated to a total dose of about 30kGy and containing thiourea, ascorbate, ascorbate/Gly-Gly, and ascorbate/lipoic acid, showed
20 recoveries of 84, 77, 88 and 86%, respectively. The samples irradiated to a total dose of about 45kGy had recoveries of 78, 81, 89 and 84%, respectively. The high molecular weight protein bands were also protected by these stabilizers.

Regarding the samples irradiated at about 4°C, for the liquid samples, thiourea appeared to afford the most effective protection. With respect to the freeze dried samples, the samples
25 irradiated to a total dose of about 30kGy and containing ascorbate, ascorbate/Gly-Gly and ascorbate/lipoic acid had recoveries of 99, 85 and 88% respectively. The samples irradiated to a total dose of about 45kGy and containing ascorbate, ascorbate/Gly-Gly and ascorbate/lipoic acid had recoveries of 83, 81 and 85% respectively.

Example 20

In this experiment, the effects of gamma irradiation on *Clostridium sordellii* in bovine bone was investigated.

Methods:

Freeze-dried vials of *Clostridium sordellii* purchased from ATCC were placed in a bovine bone that contained four holes with a diameter slightly greater than the circumference of the vials that extended to the midpoint of the bone. The bone containing the vials was then irradiated at 1.5kGy/hr with 0, 25 or 50 kGy of gamma radiation at either 4°C or on dry ice. The contents of the vials were then resuspended in 10 mL of Reinforced Clostridial Medium supplemented with Oxyrase to provide an anaerobic environment. Serial ten-fold dilutions were made to a dilution of 10⁻⁹. Fifty microliters of each dilution was then spread on a plate containing Reinforced Clostridial Medium plus 1.5% agar. A BBL GasPak Anaerobic System was used to provide an anaerobic environment for growth of the plated bacteria. The broth cultures and the plates were incubated at 37°C for 48 hours. Following incubation turbidity was visualized and absorbance readings were taken at 620 nm in the broth cultures and colonies were counted on the plates. Similar cultures of *Staph. epidermidis* and *E. coli* were also set up and irradiated. These cultures were prepared using media and conditions conventional for the organisms.

Results:

Unirradiated tubes of *Clostridium sordellii* showed frank growth as detected by obvious turbidity at dilutions ranging from the Stock suspension to 10⁻⁸. When exposed to 25 kGy at 4°C, all tubes were clear of growth from 10⁻¹ to 10⁻⁹. Only the undiluted Stock suspension showed signs of growth. When the irradiation dose was increased to 50 kGy, no growth was observed in any of the tubes. Similar results were seen for the materials irradiated on dry ice. These results are shown in the following table:

Bacteria	Description	Temperature	Log reduction 25 kGy	Log reduction 50 kGy
<i>S. epidermidis</i>	Gram Positive	4 °C	>6.0*	>6.0*
<i>E. coli</i>	Gram Negative	4 °C	>7.1*	>7.1*
<i>C. sordellii</i>	Spore Former	4 °C	6.3	>8.0*
<i>C. sordellii</i>	Spore Former	-72 °C to -76 °C	4.5	>8.0*

*: Maximum reduction detectable in the assay

Example 21

In this experiment, the effects of physical agitation on dye penetration into human bone and porcine anterior cruciate ligament (ACL) were investigated.

Method:**5 Materials and Equipment:**

- (a) 2.54 mM crystal violet (Sigma #C-6158) solution in water;
- (b) Dimethyl sulfoxide (DMSO), density = 1.1 g/ml (Sigma #D-1435);
- (c) DMSO solution (20% w/v) made with 4.545 ml DMSO in 20.455 ml crystal violet solution;
- 10 (d) Polysorbate 80 (Tween 80, Spectrum #PO138) made at 1% (v/v) and 0.1% (v/v) with crystal violet solution;
- (e) Human bone;
- (f) Porcine anterior cruciate ligament;
- (g) Lab Line Shaker; and
- 15 (h) Branson 2510 sonicator bath.

Procedure:

One piece of human bone (approximately 1 cm in length and 0.5 mm in width and height) and ligament (approximately 0.5 cm in length) were placed in 15 ml conical tubes. The following solutions were added to the tubes, in duplicate, to give two sets of samples:

- 20 (a) 20% DMSO solution with crystal violet;
- (b) 1% Tween with crystal violet solution;
- (c) 0.1% Tween with crystal violet solution; and
- (d) crystal violet solution.

One set of samples were placed in the sonicator and sonicated for approximately 4 hours.

- 25 The other set of samples were placed in the shaker for approximately 4 hours at 50°C and 375 rpm. Following sonication or shaking, the samples were removed and stored at 4°C overnight. The samples were then cut in half to examine the penetration of crystal violet dye into the bone and ligaments.

Results:

- 30 By visual inspection of the ligaments, the shaken samples showed better penetration than the sonicated samples. The order of penetration, from best to worst, was DMSO, crystal violet, 1% Tween and 0.1% Tween.

By visual inspection of the bones, the sonicated samples showed better penetration than the shaken samples. The sonicated samples appeared to have full penetration throughout the bone, whereas the shaken samples only had a ring of dye that did not penetrate the entire bone. For the shaken samples, the 1% Tween solution had the best penetration, the 20% DMSO and 0.1% Tween solutions had comparable penetration and the crystal violet solution had the worst penetration.

Example 22

In this experiment, the effects of irradiation on porcine anterior cruciate ligament in the presence of 10, 20 or 30% DMSO and various stabilizers and stabilizer mixtures irradiated at -80°C to a total dose of 50 kGy was investigated.

Materials:

Stock Solutions:

- (a) 2M sodium ascorbate in water (Spectrum S1349);
- (b) 0.5M coumaric acid (Sigma C4400, 51k3660);
- (c) 0.5M n-propylgallate (Sigma P3130, 117H0526); and
- (d) Dimethyl sulfoxide (DMSO) (JT Baker 9224-01 H40630C).

Method:

Samples of ACL in the following solvents were prepared in duplicate (one set to be irradiated and one set not to be irradiated):

- (a) 10% DMSO;
- (b) 20% DMSO;
- (c) 30% DMSO;
- (d) 10% DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid;
- (e) 20% DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid;
- (f) 30% DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid;
- (g) 10% DMSO + 100 mM thiourea;
- (h) 20% DMSO + 100 mM thiourea; and
- (i) 30% DMSO + 100 mM thiourea.

The ACL's were incubated overnight with shaking at about 4°C. Following incubation, the samples were decanted and fresh solutions were added. The samples were then incubated overnight at about -80°C and one set was irradiated to a total dose of 50kGy at a dose rate of 1.53kGy/hr. The other set of samples was not irradiated.

- 5 The ligaments were then washed with DPBS, cut into small samples, weighed and placed into tubes. 1.3 ml of 0.5M acetic acid was added to each tube. Pepsin was added to each tube at a 1:10 ratio of enzyme:tissue in 0.5M acetic acid and the samples were incubated overnight on a nutator at about 4°C.

- 10 Following incubation, the pepsin-digested supernatant was decanted and NaCl from a 5M stock solution was added to a final concentration of 1M. The supernatants were then centrifuged for about 30 minutes at 18,300 rpm at about 4°C. Collagen gel pellets were resuspended in 1 ml of 0.5M acetic acid with gentle mixing at 4°C and dialyzed against 5 mM acetic acid.

These samples were analyzed by SDS-PAGE analysis and a turbidity assay.

Results:

- 15 According to SDS-PAGE analysis, the purified pepsin digested collagen from ACL irradiated at -80°C with 10%DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid showed the best recovery. The yields for samples treated with 10%DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid, 20%DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid and 30%DMSO + 200 mM sodium ascorbate + 100 mM n-propylgallate + 100mM coumaric acid were 90%, 88% and 80%, respectively. For thiourea, the yield for samples containing 10% DMSO + 100 mM thiourea, 20% DMSO + 100 mM thiourea and 30% DMSO + 100 mM thiourea were 87%, 76% and 67%, respectively. See figure 15.

Example 23

- 25 In this experiment, the effects of various stabilizers on human femur as measured by a three point bending test were investigated.

Methods:

Blocks of human femur measuring 5mm x 5mm x 10mm were cut using a bone saw equipped with diamond edged blade.

- 30 Femur samples were prepared as follows:

(1) Sample treatment +A: samples were soaked in 200mM ascorbate for about 24 hours and then either not irradiated or irradiated at about 5.2°C at a dose rate of about 1.6kGy/hr to a total dose of either 25kGy or 50kGy;

(2) Sample treatment -A: samples were soaked in water for about 24 hours; and then
5 either not irradiated or irradiated at about 5.2°C at a dose rate of about 1.6kGy/hr to a total dose of either 25kGy or 50kGy;

(3) Sample treatment +A/a.d.: samples were soaked in 200mM ascorbate for about 24 hours, air-dried overnight and then either not irradiated or irradiated as air-dried bone at a dose rate of about 1.6kGy/hr to a total dose of either 25kGy (at about 4.1°C) or 50kGy (at about 6.1°C);

(4) Sample treatment -A/a.d.: samples were soaked in water for about 24 hours, air-dried overnight and then either not irradiated or irradiated as air-dried bone at a dose rate of about 1.6kGy/hr to a total dose of either 25kGy (at about 4.1°C) or 50kGy (at about 6.1°C);

(5) Sample treatment +CK2: samples were soaked in a cryoprotectant cocktail containing 100mM trehalose, 150mM mannitol, 24.2%DMSO, 16.8% butanediol and 14%
15 formamide for about 24 hours, quick frozen in a dry-ice/ethanol bath and then either not irradiated or irradiated at about -72°C at a dose rate of about 2.45kGy/hr to a total dose of either 25kGy or 50kGy;

(6) Sample treatment -CK2: samples were soaked in 24.2%DMSO for about 24 hours, quick frozen in a dry-ice/ethanol bath and then either not irradiated or irradiated at about -
20 72°C at a dose rate of about 2.45kGy/hr to a total dose of either 25kGy or 50kGy;

(7) Sample treatment +CK1: samples were soaked in polypropylene glycol (PPG) overnight, removed from PPG and wiped of excess PPG. The samples were then soaked in a stabilizer cocktail containing 100µM trolox, 100mM coumaric acid, 100mM lipoic acid and 100mM propyl gallate for about 24 hours, quick frozen in a dry-ice/ethanol bath and then either not
25 irradiated or irradiated at about -72°C at a dose of about 2.45kGy/hr to a total dose of either 25kGy or 50kGy (samples +CK1); and

(8) Sample treatment -CK1: samples were soaked in PPG overnight, removed from PPG and wiped of excess PPG. The samples were then either not irradiated or irradiated at about -72°C at a dose of about 2.45kGy/hr to a total dose of either 25kGy or 50kGy.

30 Following treatment as outlined above, the samples were subjected to a three point bending test. The results and test are presented in the following table:

3 Point Bending Test of Human Femur

$$\sigma_b = (3PL)/(2bh^2)$$

where:

σ_b = bending stress (MPa);

5 P = maximum load bone (N);

L = support span (12.6mm);

b = sample width (mm); and

h = sample height (mm).

SampleTreatment	Total Dose	Ave σ_b	Std Dev
+A	0	204.310	24.229
	25	160.299	20.320
	50	114.695	19.115
-A	0	180.402	14.706
	25	138.366	41.132
	50	125.557	9.180
+CK2	0	217.925	13.033
	25	207.496	16.058
	50	186.578	30.182
-CK2	0	194.240	21.253
	25	176.385	11.249
	50	144.499	28.051
+A/a.d.	0	184.969	43.349
	25	146.857	14.741
	50	78.102	24.446
-A/a.d.	0	182.516	34.202
	25	139.275	16.984
	50	88.670	10.876
+CK1	0	190.267	24.822
	25	172.056	7.042
	50	132.895	16.209
-CK1	0	190.014	17.244
	25	148.423	8.087
	50	110.263	15.832

Example 24

In this experiment, the effects of gamma radiation on liquid and gel collagen samples irradiated at about -20°C at a dose rate of about 1.486kGy/hr to a total dose of 45kGy.

Methods:

5 The following stock solutions were prepared:

- (1) 2M sodium ascorbate (Spectrum S1349 QP 0839) in water;
- (2) 0.24M L-methionine (Sigma M6039 88H11341) in water;
- (3) 1M Gly-Gly (Sigma G3915 127H54052) in water; and
- (4) 1M thiourea (Sigma T8656 11k01781) in water.

10 Samples were prepared in the final volume of 1ml for irradiation. Samples were prepared by adding 0.5ml of 40mM NaCl with 0.5ml liquid or gel collagen (1mg/ml) in the presence of the following stabilizers:

- (1) Control: collagen (0.5mg/ml);
- (2) Collagen (0.5mg/ml) + 50mM ascorbate;
- 15 (3) Collagen (0.5mg/ml) + 50mM ascorbate + 50mM Gly-Gly;
- (4) Collagen (0.5mg/ml) + 25mM thiourea; and
- (5) Collagen (0.5 mg/ml) + 25mM methionine.

The gel samples were incubated for about 30 minutes at room temperature after mixing with phosphate buffer. The liquid collagen samples were kept at about 4°C to prevent gelling.
20 Then, both gel and liquid collagen samples were frozen at -20°C and irradiated at -20°C at a dose rate of about 1.486kGy/hr to a total dose of about 45kGy.

The samples were analyzed by SDS-PAGE and a turbidity assay.

Results:

According to SDS-PAGE, the samples containing ascorbate + Gly-Gly showed recoveries
25 of 77% for gel collagen and 81% for liquid collagen. The samples containing thiourea showed recoveries of 80% for gel collagen and 87% for liquid collagen.

From turbidity data, thiourea appeared to be the best stabilizer in protecting either gel or liquid collagen at -20°C .

Example 25

In this experiment, the protective effects of various stabilizers on porcine anterior cruciate ligament (ACL) irradiated at about -72°C to a total dose of about 50kGy were investigated.

Methods:

5 The following stock solutions were prepared:

(1) 400mM propyl gallate (Sigma P-3130, lot 60K0877) and 400mM butylated hydroxyanisole (BHA) (Sigma B-1253, lot 19H0261) in 100% DMSO;

(2) 400mM N-t-butyl- α -phenyl nitron (BPN) (Sigma B-7263, lot 60K1191) in 50% DMSO;

10 (3) 100mM curcumin (Sigma C-1386, lot 100K3447) in 50% DMSO;

(4) 200mM probucol (Sigma P-9672, lot 128H0695) in 50% PPG and 50% tocopherol;
and

(5) 400mM Trp-Ala (Sigma T-8152, lot 129F58502) in 100% DMSO.

15 Following dehydration with PPG, the ligaments were blotted to remove excess PPG and placed in 2ml serum vials. Stabilizers were added to the following final concentrations in duplicate (one set will receive 0kGy irradiation and the other will receive 50kGy):

(1) 200mM propyl gallate and 200mM BHA in 50% DMSO;

(2) 200mM BPN in 25% DMSO;

(3) 100mM curcumin in 50% DMSO;

20 (4) 200mM probucol in 50:50 PPG:Tocopherol;

(5) 200mM Trp-Ala in 50% DMSO; and

(6) Control, 50% DMSO.

25 The vials were then nutated at about 4°C for about 136 hours. Following nutation, the samples were quick frozen in a dry-ice/ethanol bath and stored at about -80°C . One set of samples were then irradiated at about -72°C at a dose rate of about 1.35kGy/hr to a total dose of about 50kGy and the other set was not irradiated.

Following irradiation, the samples were treated as follows:

- (1) the samples were washed 5 times with PBS to remove the stabilizers and stored in PBS at about 4°C;
- (2) a small piece from the center of the ligament was cut, pressed to remove excess PBS and quick frozen on a dry-ice/ethanol bath;
- 5 (3) the frozen ligaments were then minced with a razor blade and weighed;
- (4) 20x (w/v) of 0.5N acetic acid and pepsin at 1:10 (w/w substrate to enzyme) were added to the samples and the samples were digested for about 24 hours at about 4°C with vigorous shaking.
- (5) another volume of pepsin was added to the samples and the samples were
10 digested for about 24 hours at about 4°C with vigorous shaking;
- (6) 200µl of 0.5N acetic acid were added to the samples;
- (7) the samples were centrifuged for about 1 hour at 4°C and 20,000 rpm;
- (8) following centrifugation, the supernatant was removed and the collagen was precipitated by adding NaCl to 2M;
- 15 (9) the samples were then vigorously shaken for 3 hours at 4°C, placed on an ice bath for 3 hours without shaking and centrifuged at 20,000 rpm for 1 hour at 4°C; and
- (10) the pellets were solubilized with 0.5N acetic acid overnight on a nutator at 4°C.

Results:

20 Irradiating at low temperature in the presence of stabilizers results in improved recovery compared to samples not containing stabilizers. Particularly good recovery was observed with the samples containing probucol in 50:50 PPG:tocopherol irradiated to about 50kGy.

Experiment 26

25 In this experiment, the effects of "fast freezing" as compared to "slow freezing" on porcine heart valves in the presence or absence of various cryopreservatives irradiated at a dose rate of about 5.109kGy/hr to a total dose of 50 kGy at about -72°C were investigated.

Methods:

The following stock solutions were prepared:

- (1) 1M trehalose (Sigma T-9531, lot 61K7026);

- (2) 1M KH_2PO_4 (Sigma P-5655, lot 41H07875);
(3) 1M K_2HPO_4 (Sigma P-2222, lot 80K1035);
(4) 1M KCl (Sigma P-5405, lot 52H6876);
(5) 1M mannitol (Sigma M-849, lot 106H00842);
5 (6) 1M NaHCO_3 (Sigma 5761); and
(7) 2M sodium ascorbate (Spectrum S 1349, lot QP0839).

Additionally, the following reagents were employed:

- (1) ethanol (Spectrum S1349, lot QP0839);
(2) DMSO (J.T. Baker, 9224-01, lot K50664);
10 (3) 1,2-propanediol (Aldrich 39,803-9, lot 09521HO);
(4) formamide (EM Science, 4650, lot 3631B33); and
(5) PBS.

A cryopreservative mixture to the following final concentrations was prepared:

	Trehalose	100mM
15	KH_2PO_4	15mM
	K_2HPO_4	42mM
	KCl	15mM
	NaHCO_3	10mM
	mannitol	150mM
20	DMSO	24.2%
	1,2-propanediol	16.8%
	formamide	14.0%

Frozen porcine heart valves were thawed on ice and the 3 cusps from were dissected. The cusps were rinsed in PBS and transferred to 2ml irradiation vials. 900 μl of the cryopreservative
25 mixture were added to the samples. 100 μl of H_2O were added to half of the samples (designated –
Asc samples) and 100 μl sodium ascorbate was added to the other half of the samples.

Samples were either slow frozen or fast frozen, as follows:

(1) Slow freezing: the vials were placed without stoppers into a freeze dryer and frozen to about -65°C at a rate of approximately $-1^{\circ}\text{C}/\text{min}$; and

(2) Fast freezing: the vials were quick frozen in less than about 5 minutes in a dry-ice/ethanol bath.

5 Following freezing, half of the samples were irradiated at about -72°C at a dose rate of about 5.1kGy/hr to a total dose of 50kGy.

Following irradiation, the samples were analyzed by SDS-PAGE analysis, western blotting with anti-decorin and anti-fibronectin, and uronic acid determination.

Results:

10 According to SDS-PAGE analysis, the irradiated samples had an increase in the intensity of the lowest molecular weight band of the triplet observed at about 130kDa. There appeared not to be significant differences between samples that were slow frozen and those that were fast frozen. Additionally, the irradiated samples showed good recovery of the pentuplet band at about 205kDa. See figures 16-20.

15 Western blotting with anti-decorin showed weaker staining of the band at about 116kDa for the irradiated samples as compared to the unirradiated samples. The antifibronectin antibody showed weaker reactivity with three or four of the bands at about 220kDa in the irradiated samples as compared to the unirradiated samples.

All irradiated samples had less total uric acid than their unirradiated controls (43-74%).
20 The fast frozen samples irradiated in the presence of the stabilizer mixture and ascorbate showed recovery of about 74%.

Example 27

In this experiment, the effects of various cryopreservatives on porcine heart valves irradiated to about 50kGy at about -80°C in the presence or absence of sodium ascorbate were
25 investigated.

Methods:

Dissected porcine heart valve cusp samples were divided into two groups. The groups were treated with one of the following solutions:

(1) Solution CP1 containing 10% FCS, Penicillin-streptomycin, M199 and 2M DMSO;
30 and

(2) Solution CP2 containing 100mM trehalose, 15mM KH₂PO₄, 42mM K₂HPO₄, 15mM KCl, 10mM NaHCO₃, 150 mM mannitol, 24.2% DMSO, 16.8% 1,2-propanediol, and 14% formamide.

In addition, 200 mM sodium ascorbate (Asc) was added to half of the samples containing solution CP1 and half of the samples containing solution CP2 to give the following four sets of samples: CP1+Asc, CP1-Asc, CP2+Asc and CP2-Asc. For each of these sets, half of the samples were fast frozen and half were slow frozen, in duplicate. (See Example 26). One set of these samples was irradiated to 50kGy at about -80°C and the other set was not irradiated.

Following irradiation, the heart valve cusps were minced into small pieces and resuspended in 1 ml of 0.5N acetic acid. Pepsin was added to these pellets at a 1:10 ratio of enzyme:tissue in 0.5N acetic acid. The samples were incubated at about 4°C on the nutator for 2 days. Following incubation, another portion of pepsin was added to each sample and the samples were incubated on the nutator overnight at about 4°C.

The pepsin digests were then centrifuged at 22,000 rpm at 4°C for 30 minutes. Following centrifugation, 5M NaCl was added to the supernatants to a final concentration of 1M. The supernatants were then centrifuged at 22,000 rpm for 30 min at 4°C. The collagen pellets were then resuspended in 1ml of 0.5N acetic acid with gentle mixing at 4°C. 10µg of the pepsin digested collagen from each sample were run on 4-12% gel.

The pepsin digested collagens were dialyzed against 5mM acetic acid, and absorption was measured at 218nm.

Results:

From the SDS-PAGE, purified pepsin digested collagen treated from samples treated with solution CP2 showed better recovery than samples treated with solution CP1. For these samples, the yield for collagen α-chain was 93.7% for the slow freeze samples and >100% for the fast freeze samples. The inclusion of ascorbate appeared to increase the recovery somewhat for all samples.

Example 28

In this experiment, the effects of "fast freezing" as compared to "slow freezing" on porcine heart valves in the presence or absence of various cryopreservative with or without sodium ascorbate irradiated at a dose rate of about 5.13kGy/hr to a total dose of 50 kGy at about -72°C were investigated.

Methods:

The following stock solutions were prepared:

(1) Freeze medium (M199/FCS/P-S):

fetal calf serum (FCS) (10%) = 50ml

5 penicillin-streptomycin (P-S) = 2.5 ml

M199 = QS 500ml;

(2) 2M DMSO solution:

DMSO = 15.62g

Freeze medium = QS 100ml. and

10 (3) 3M DMSO solution:

DMSO = 23.44g

Freeze medium = QS 100ml

15 Frozen porcine heart valves were thawed on ice. The three heart cusps were then dissected out and placed in 2 ml irradiation vials. Half of the samples were treated with the 2M DMSO solution and the other half were treated with the 3M DMSO solution. For each set of samples, 100 μ l of H₂O were added to half of the samples and 100 μ l of 2M sodium ascorbate were added to the other half. Half of the samples were fast frozen and half were slow frozen. (See Example 26).

20 The samples were then irradiated at about -72°C at a dose rate of about 5.14kGy/hr to a total dose of 50kGy. Control samples were not irradiated.

Following irradiation, the samples were washed several times with approximately 30ml of cold PBS and incubated on ice for about 30-45 minutes. The samples were washed and incubated a total of 5 times. After the final wash, 2 cusps from each sample were transferred into eppendorfs containing 1ml cold PBS and the third cusp was transferred to a separate eppendorf reserved for 25 histological analysis also containing 1ml cold PBS.

Each cusp was then washed 6 times with acetone in the eppendorf (approximately 1.5ml per wash) and subjected to vacuum drying, with no heat, for about 15 minutes, or until dry. The samples were then weighed and hydrolized at a ratio of 10mg tissue to 1ml 6N.HCl. Following

hydrolysis, the samples were centrifuged at 4,000 rpm for about 10 minutes. The supernatants were transferred into clean eppendorfs.

The samples were analyzed by SDS-PAGE.

Results:

- 5 SDS-PAGE analysis showed that there was no clear difference between cusps that were fast frozen and those that were slow frozen in either the 2M DMSO solution or the 3M DMSO solution. The presence or absence of ascorbate appeared not to impact recovery. See Figure 21-23.

- 10 Having now fully described this invention, it will be understood to those of ordinary skill in the art that the methods of the present invention can be carried out with a wide and equivalent range of conditions, formulations and other parameters without departing from the scope of the invention or any embodiments thereof.

- 15 All patents and publications cited herein are hereby fully incorporated by reference in their entirety. The citation of any publication is for its disclosure prior to the filing date and should not be construed as an admission that such publication is prior art or that the present invention is not entitled to antedate such publication by virtue of prior invention.

WHAT IS CLAIMED IS

1. A method for sterilizing one or more tissues that are sensitive to radiation, said method comprising:
- 5 (i) adding to said one or more tissues at least one stabilizer; and
- (ii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues, wherein said at least one stabilizer and the rate of irradiation are together effective to protect said one or more tissues from said radiation.
- 10
2. A method for sterilizing one or more tissues that are sensitive to radiation, said method comprising:
- (i) adding to said one or more tissues at least one cryopreservative; and
- (ii) irradiating said one or more tissues with radiation for a time effective to sterilize
- 15 said one or more tissues and at a rate effective to sterilize said one or more tissues.
3. A method for sterilizing one or more tissues that are sensitive to radiation, said method comprising:
- (i) adding to said one or more tissues at least one stabilizer;
- 20 (ii) subjecting said one or more tissues to a treatment effective to enhance penetration of said at least one stabilizer into said one or more tissues; and
- (iii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues, wherein said at least one stabilizer and the rate of irradiation are together effective to
- 25 protect said one or more tissue from said radiation.
4. A method for sterilizing one or more tissues that are sensitive to radiation, said method comprising:
- (i) adding to said one or more tissues at least one cryopreservative;
- 30 (ii) subjecting said one or more tissues to a treatment effective to enhance penetration of said at least one cryopreservative into said one or more tissues; and
- (iii) irradiating said one or more tissues with radiation for a time effective to sterilize said one or more tissues and at a rate effective to sterilize said one or more tissues.

5. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is not more than about 3.0 kGy/hour.
- 5 6. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is not more than about 2.0 kGy/hr.
7. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is not more than about 1.0 kGy/hr.
- 10 8. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is not more than about 0.3 kGy/hr.
9. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is more than
15 about 3.0 kGy/hour.
10. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is at least about 6.0 kGy/hour.
- 20 11. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is at least about 18.0 kGy/hour.
12. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is at least about 30.0 kGy/hour.
- 25 13. The method according to one of claims 1, 2, 3 or 4, wherein said effective rate is at least about 45 kGy/hour.
14. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues is
30 maintained in a low oxygen atmosphere.
15. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues is maintained in an atmosphere comprising at least one noble gas or nitrogen.

16. The method according to claim 15, wherein said noble gas is argon.
17. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues is treated prior to irradiation with at least one cycle of being subjected to a vacuum and then being placed under an atmosphere comprising at least one noble gas or nitrogen.
18. The method according to claim 17, wherein said one or more tissues is treated prior to irradiation with at least 3 cycles of being subjected to a vacuum and then being placed under an atmosphere comprising at least one noble gas or nitrogen.
19. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 15%.
20. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 10%.
21. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 3%.
22. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 2%.
23. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 1%.
24. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 0.5%.
25. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues have a residual solvent content of less than about 0.08%.
26. The method according to one of claims 1, 2, 3 or 4, wherein at least one sensitizer is added to said one or more tissues prior to said step of irradiating said one or more tissues.

27. The method according to one of claims 1 or 3, wherein said at least one stabilizer is an antioxidant.
28. The method according to one of claims 1 or 3, wherein said at least one stabilizer is a free radical scavenger or spin trap.
29. The method according to one of claims 1 or 3, wherein said at least one stabilizer is a combination stabilizer.
30. The method according to one of claims 1 or 3, wherein said at least one stabilizer is a ligand.
31. The method according to claim 30, wherein said ligand is heparin or copper.
32. The method according to one of claims 1 or 3, wherein said at least one stabilizer reduces damage due to reactive oxygen species.
33. The method according to one of claims 1 or 3, wherein said at least one stabilizer is selected from the group consisting of: ascorbic acid or a salt or ester thereof; glutathione; vitamin E or a derivative thereof, including Trolox; albumin; sucrose; glycylglycine; L-carnosine; cysteine; silymarin; diosmin; hydroquinonesulfonic acid; 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid; uric acid or a salt or ester thereof; methionine; histidine; N-acetyl cysteine; lipoic acid; sodium formaldehyde sulfoxylate; gallic acid or a derivative thereof; propyl gallate; ethanol; acetone; rutin; epicatechin; biacalein; purpurogallin; coumaric acid; deferoxamine; ergothionine; thiourea; trehalose; polylysine; dimethylurea; mercaptoethylamine; dimethyl-2-thiourea, 2,3-butanediol, probuchol, curcumin and mixtures of two or more thereof.
34. The method according to claim 33, wherein said mixtures of two or more stabilizers are selected from the group consisting of: mixtures of ethanol and acetone; mixtures of ascorbic acid, or a salt or ester thereof, and uric acid, or a salt or ester thereof; mixtures of ascorbic acid, or a salt or ester thereof, and 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid; mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, and 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid; mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid, and albumin;

mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid, albumin and sucrose; mixtures of ascorbic acid, or a salt or ester thereof, and glycylglycine; mixtures of ascorbic acid, or a salt or ester thereof, glycylglycine and albumin; mixtures of ascorbic acid, or a salt or ester thereof, and L-carnosine;
5 mixtures of ascorbic acid, or a salt or ester thereof, and cysteine; mixtures of ascorbic acid, or a salt or ester thereof, and N-acetyl cysteine; mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid, and silymarin; mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid, and diosmin; mixtures of ascorbic acid, or a
10 salt or ester thereof, uric acid, or a salt or ester thereof, and lipoic acid; mixtures of ascorbic acid, or a salt or ester thereof, uric acid, or a salt or ester thereof, and hydroquinonesulfonic acid; mixtures of Trolox, α -lipoic acid, coumaric acid and n-propyl gallate; and mixtures of uric acid, or a salt or ester thereof, lipoic acid, sodium formaldehyde sulfoxylate, gallic acid, or a derivative thereof, propyl gallate, and 6-hydroxy-2,5,7,8-tetramethylchroman-2-carboxylic acid.

15

35. The method according to one of claims 1 or 3, wherein said at least one stabilizer is a dipeptide stabilizer.

20

36. The method according to claim 35, wherein said dipeptide stabilizer is selected from the group consisting of glycyl-glycine (Gly-Gly), carnosine and anserine.

37. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is corpuscular radiation, electromagnetic radiation, or a mixture thereof.

25

38. The method according to claim 37, wherein said electromagnetic radiation is selected from the group consisting of radio waves, microwaves, visible and invisible light, ultraviolet light, x-ray radiation, gamma radiation and combinations thereof.

30

39. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is gamma radiation.

40. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is E-beam radiation.

41. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is visible light.
42. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is ultraviolet light.
- 5 43. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is x-ray radiation.
- 10 44. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is polychromatic visible light.
45. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is infrared.
- 15 46. The method according to one of claims 1, 2, 3 or 4, wherein said radiation is a combination of one or more wavelengths of visible and ultraviolet light.
47. The method according to one of claims 1, 2, 3 or 4, wherein said irradiation is conducted at ambient temperature.
- 20 48. The method according to one of claims 1, 2, 3 or 4, wherein said irradiation is conducted at a temperature below ambient temperature.
- 25 49. The method according to one of claims 1, 2, 3 or 4, wherein said irradiation is conducted below the freezing point of at least one or more solvents within or surrounding said one or more tissues.
- 30 50. The method according to one of claims 1, 2, 3 or 4, wherein said irradiation is conducted below the eutectic point of at least one or more solvents within or surrounding said one or more tissues.
51. The method according to one of claims 1, 2, 3 or 4, wherein said irradiation is conducted at a temperature above ambient temperature.

52. The method according to one of claims 1 or 3, further comprising adding at least one cryopreservative to said one or more tissues prior to irradiation.

53. The method according to claim 52, wherein said at least one cryopreservative is also a stabilizer.

54. The method according to one of claims 2 or 4, further comprising adding at least one stabilizer to said one or more tissues prior to irradiation.

55. The method according to claim 54, wherein said at least one stabilizer is also a cryopreservative.

56. The method according to one of claims 2 or 4, wherein said at least one cryopreservative is selected from the group consisting of chondroitin sulfate, glycosaminoglycan dimethylsulfoxide, cell penetrating organic solutes, polysaccharides, glycerol, Dulbecco's minimum essential medium, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, DMSO, trehalose, KH_2PO_4 , K_2HPO_4 , KCl, mannitol, NaHCO_3 , sodium ascorbate, 1,2-propanediol, 2,3-butanediol, probuchol, curcumin, formamide and mixtures thereof.

57. The method according to claim 56, wherein said mixtures are selected from the group consisting of: glycosaminoglycan and a cell penetrating solute; chondroitin sulfate and a cell penetrating solute; Dulbecco's minimum essential medium, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, chondroitin sulfate and DMSO; and trehalose, KH_2PO_4 , K_2HPO_4 , KCl, mannitol, NaHCO_3 , sodium ascorbate, 1,2-propanediol, 2,3-butanediol, probuchol, curcumin and formamide.

58. The method according to one of claims 2 or 4, wherein said at least one cryopreservative comprises a mixture of Dulbecco's minimum essential medium, hepes buffer, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, chondroitin sulfate and DMSO.

59. The method according to claim 3, wherein the step of subjecting said one or more tissues to a treatment effective to enhance penetration of said at least one stabilizer into said one or more tissues is selected from the group consisting of physical treatment, chemical treatment and combinations thereof.

60. The method according to claim 59, wherein said treatment comprises physical treatment.
61. The method according to claim 60, wherein said physical treatment is selected from the
5 group consisting of agitation, slow freezing, fast freezing and combinations thereof.
62. The method according to claim 61, wherein said physical treatment comprises agitation.
63. The method according to claim 62, wherein said agitation is selected from the group
10 consisting of sonication, shaking and combinations thereof.
64. The method according to claim 61, wherein said physical treatment comprises slow
freezing.
- 15 65. The method according to claim 64, wherein said slow freezing comprises cooling said one
or more tissues at a rate of about 1°C/min.
66. The method according to claim 61, wherein said physical treatment comprises fast
freezing.
- 20 67. The method according to claim 66, wherein said fast freezing comprises placing said one
or more tissues in a dry-ice/ethanol bath.
68. The method according to claim 59, wherein said treatment comprises chemical treatment.
- 25 69. The method according to claim 68, wherein said chemical treatment comprises the step of
adding to said one or more tissues at least one compound effective to increase penetration of said
at least one stabilizer into said tissue prior to irradiation.
- 30 70. The method according to claim 69, wherein said at least one compound effective to
increase penetration of said at least one stabilizer into said tissue is selected from the group
consisting of compounds that cause an increase in the distance between molecules in the tissue
and compounds that cause macromolecules in the tissue to become less compact, or relaxed.

71. The method according to claim 69, wherein said at least one compound effective to increase penetration of said at least one stabilizer into said tissue is cationic when said at least one stabilizer is anionic.

5

72. The method according to claim 69, wherein said at least one compound effective to increase penetration of said at least one stabilizer into said tissue is anionic when said at least one stabilizer is cationic.

10 73. The method according to claim 4, wherein the step of subjecting said one or more tissues to a treatment effective to enhance penetration of said at least one cryopreservative into said one or more tissues is selected from the group consisting of physical treatment, chemical treatment and combinations thereof.

15 74. The method according to claim 73, wherein said treatment comprises physical treatment.

75. The method according to claim 74, wherein said physical treatment is selected from the group consisting of agitation, slow freezing, fast freezing and combinations thereof.

20 76. The method according to claim 75, wherein said physical treatment comprises agitation.

77. The method according to claim 76, wherein said agitation is selected from the group consisting of sonication, shaking and combinations thereof.

25 78. The method according to claim 75, wherein said physical treatment comprises slow freezing.

79. The method according to claim 78, wherein said slow freezing comprises cooling said one or more tissues at a rate of about 1°C/min.

30

80. The method according to claim 75, wherein said physical treatment comprises fast freezing.

81. The method according to claim 80, wherein said fast freezing comprises placing said one or more tissues in a dry-ice/ethanol bath.

82. The method according to claim 73, wherein said treatment comprises chemical treatment.

5

83. The method according to claim 82, wherein said chemical treatment comprises the step of adding to said one or more tissues at least one compound effective to increase penetration of said at least one cryopreservative into said tissue prior to irradiation.

10 84. The method according to claim 83, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is selected from the group consisting of compounds that cause an increase in the distance between molecules in the tissue and compounds that cause macromolecules in the tissue to become less compact, or relaxed.

15 85. The method according to claim 83, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is cationic when said at least one cryopreservative is anionic.

86. The method according to claim 83, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is anionic when said at
20 least one cryopreservative is cationic.

87. A composition comprising one or more tissues and at least one cryopreservative in an amount effective to preserve said one or more tissues for their intended use following sterilization with radiation.

25 88. The composition according to claim 87, wherein said at least one cryopreservative is selected from the group consisting of chondroitin sulfate, glycosaminoglycan dimethylsulfoxide, cell penetrating organic solutes, polysaccharides, glycerol, Dulbecco's minimum essential medium, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, DMSO, glycerol, trehalose, KH₂PO₄, K₂HPO₄, KCl, mannitol, NaHCO₃, sodium ascorbate, 1,2-propanediol, 2,3-butanediol,
30 probuchol, curcumin, formamide and mixtures thereof.

89. The composition according to claim 88, wherein said mixtures are selected from the group consisting of: glycosaminoglycan and a cell penetrating solute; chondroitin sulfate and a cell penetrating solute; Dulbecco's minimum essential medium, glutamine, D-glucose, sodium pyruvate,

fetal calf serum, papaverine, chondroitin sulfate and DMSO; and trehalose, KH₂PO₄, K₂HPO₄, KCl, mannitol, NaHCO₃, sodium ascorbate, 1,2-propanediol, 2,3-butanediol, probuchol, curcumin and formamide.

5 90. The composition according to claim 87, wherein said at least one cryopreservative comprises a mixture of Dulbecco's minimum essential medium, hepes buffer, glutamine, D-glucose, sodium pyruvate, fetal calf serum, papaverine, chondroitin sulfate and DMSO.

91. A method for prophylaxis or treatment of a condition or disease or malfunction or deficit of
10 a tissue in a mammal comprising introducing into a mammal in need thereof one or more tissues sterilized according to a method according to one of claims 1, 2, 3 or 4.

92. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is greater than 100% of
15 the pre-irradiation value.

93. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 100% of the pre-irradiation value.
20

94. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 90% of the pre-irradiation value.

25 95. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 80% of the pre-irradiation value.

96. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired
30 characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 70% of the pre-irradiation value.

97. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 60% of the pre-irradiation value.

5 98. The method according to one of claims 1, 2, 3 or 4, wherein the recovery of the desired characteristic(s) of said one or more tissues after sterilization by irradiation is at least about 50% of the pre-irradiation value.

99. The method according to one of claims 1 or 3, wherein said step of adding to said one or
10 more tissues at least one stabilizer comprises at least one method selected from the group consisting of: soaking the tissue in a solution containing said at least one stabilizer, optionally under pressure, at elevated temperature and/or in the presence of a penetration enhancer; applying a gas containing said at least one stabilizer, optionally under pressure and/or at elevated temperature; injecting said at least one stabilizer or a solution containing said at least one stabilizer directly into
15 said tissue; placing said tissue under reduced pressure and then introducing a gas or solution at a higher pressure containing said at least one stabilizer; dehydrating said tissue and rehydrating said tissue with a solution containing said at least one stabilizer; applying a high ionic strength solvent containing said at least one stabilizer, optionally followed by a controlled reduction in the ionic strength of said solvent; cycling said tissue between solutions of high ionic and/or osmolar strength
20 and solutions of low ionic and/or osmolar strength containing said at least one stabilizer; applying the stabilizer within or as a component of a microemulsion; and combinations of two or more thereof.

100. The method according to one of claims 2 or 4, wherein said step of adding to said one or
25 more tissues at least one cryopreservative comprises at least one method selected from the group consisting of: soaking the tissue in a solution containing said at least one cryopreservative, optionally under pressure, at elevated temperature and/or in the presence of a penetration enhancer; applying a gas containing said at least one cryopreservative, optionally under pressure and/or at elevated temperature; injecting said at least one cryopreservative or a solution containing
30 said at least one cryopreservative directly into said tissue; placing said tissue under reduced pressure and then introducing a gas or solution at a higher pressure containing said at least one cryopreservative; dehydrating said tissue and rehydrating said tissue with a solution containing said at least one cryopreservative; applying a high ionic strength solvent containing said at least one cryopreservative, optionally followed by a controlled reduction in the ionic strength of said solvent;

cycling said tissue between solutions of high ionic and/or osmolar strength and solutions of low ionic and/or osmolar strength containing said at least one cryopreservative; applying the cryopreservative within or as a component of a microemulsion; and combinations of two or more thereof.

5

101. The method according to one of claims 1, wherein said step of adding to said one or more tissues at least one stabilizer further comprises adding at least one compound effective to increase penetration of said at least one stabilizer into said tissue.

10

102. The method according to claim 101, wherein said at least one compound effective to increase penetration of said at least one stabilizer into said tissue is selected from the group consisting of compounds that cause an increase in the distance between molecules in the tissue and compounds that cause macromolecules in the tissue to become less compact, or relaxed.

15

103. The method according to claim 101, wherein said at least one compound effective to increase penetration of said at least one stabilizer into said tissue is cationic when said at least one stabilizer is anionic.

20

104. The method according to claim 101, wherein said at least one compound effective to increase penetration of said at least one stabilizer into said tissue is anionic when said at least one stabilizer is cationic.

25

105. The method according to one of claims 2, wherein said step of adding to said one or more tissues at least one cryopreservative further comprises adding at least one compound effective to increase penetration of said at least one cryopreservative into said tissue.

30

106. The method according to claim 105, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is selected from the group consisting of compounds that cause an increase in the distance between molecules in the tissue and compounds that cause macromolecules in the tissue to become less compact, or relaxed.

107. The method according to claim 105, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is cationic when said at least one cryopreservative is anionic.

108. The method according to claim 105, wherein said at least one compound effective to increase penetration of said at least one cryopreservative into said tissue is anionic when said at least one cryopreservative is cationic

5

109. The method according to one of claims 1, 2, 3 or 4, wherein said step of irradiating said one or more tissues produces substantially no neo-antigens therein.

10

110. The method according to one of claims 1, 2, 3 or 4, wherein said step of irradiating said one or more tissues reduces the number of reactive allo-antigens and/or xeno-antigens and/or reduces the severity of the recipient's bodies response to said antigens.

111. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are packaged prior to said irradiation.

15

112. A composition comprising one or more tissues prepared according to a method of one of claims 1, 2, 3 or 4.

20

113. The method according to one of claims 1, 2, 3 or 4, wherein said step of irradiating said one or more tissues reduces the number of neo-antigens therein.

114. The method according to claim 68, wherein said chemical treatment comprises treating said at least one tissue with a microemulsion.

25

115. The method according to claim 82, wherein said chemical treatment comprises treating said at least one tissue with a microemulsion.

30

116. A composition comprising one or more tissues, at least one penetration enhancer and at least one cryopreservative in an amount effective to preserve said one or more tissues for their intended use following sterilization with radiation.

117. The composition according to claim 87, further comprising at least one stabilizer.

118. The composition according to claim 117, wherein said at least one stabilizer is also a cryopreservative.

119. The composition according to claim 87, wherein said at least one cryopreservative is also a stabilizer.

120. A composition comprising one or more tissues and at least one stabilizer in an amount effective to protect said one or more tissues for their intended use following sterilization with radiation.

121. The composition according to claim 120, further comprising at least one cryopreservative.

122. The composition according to claim 121, wherein said at least one cryopreservative is also a stabilizer.

123. The composition according to claim 120, wherein said at least one cryopreservative is also a stabilizer.

124. A composition comprising one or more tissues, at least one stabilizer, at least one non-aqueous solvent and at least one cryopreservative in an amount effective to preserve said one or more tissues for their intended use following sterilization with radiation.

125. The composition according to claim 124, wherein said at least one stabilizer is also a cryopreservative.

126. The composition according to claim 124, wherein said at least one cryopreservative is also a stabilizer.

127. The composition according to claim 124, wherein said non-aqueous solvent is a cryopreservative and a stabilizer.

128. The composition according to claim 127, wherein said non-aqueous solvent is DMSO.

129. A composition comprising one more tissues having a reduced water content and at least one cryopreservative in an amount effective to preserve said one or more tissues for their intended use following sterilization with radiation.

5 130. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are irradiated to a total dose of at least about 25kGy.

131. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are irradiated to a total dose of at least about 45kGy.

10

132. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are irradiated to a total dose of at least about 50kGy.

133. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are
15 irradiated to a total dose of at least about 75kGy.

134. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are irradiated to a total dose of at least about 100kGy.

20 135. The method according to one of claims 1, 2, 3 or 4, wherein said one or more tissues are irradiated to a total dose of about 50kGy.

136. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is from about 2 to about 11.

25

137. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is from about 3 to about 9.

138. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more
30 tissues is from about 4 to about 7.

139. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is about 3.

140. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is about 5.

141. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is about 7.

142. The method according to one of claims 1, 2, 3 or 4, wherein the pH of said one or more tissues is about 9.


143. The method according to one of claims 1, 2, 3 or 4, wherein the pH of the one or more tissues is at or near the isoelectric point of one or more components thereof.

144. A composition comprising one or more tissues treated according to the method of one of claims 1, 2, 3 or 4, wherein said one or more tissues exhibit lower neo-antigenicity than tissue not so treated.

145. A composition comprising one or more tissues treated according to the method of one of claims 1, 2, 3 or 4, wherein said one or more tissues exhibit a lower pathogen content than tissue not so treated.


1/54

FIG. 1A



2/54

FIG. 1B



3/54






FIG. 1D

REDUCED




5/54




6/54

FIG. 2B




7/54

FIG. 2C




8/54



9/54

FIG. 2E


REDUCED



1 2 3 4 5 6 7 8 9


10/54

FIG. 3A




11/54

FIG. 3B




12/54

FIG. 3C




13/54



14/54

FIG. 3E


REDUCED



1 2 3 4 5 6 7 8 9


15/54

FIG. 4A




16/54

FIG. 4B




17/54

FIG. 4C




18/54

FIG. 4D




19/54

FIG. 4E



20/54


FIG. 4F



21/54

FIG. 4G


1. Molecular Weight Markers
2. PBS, 0 kGy
3. PBS, 45 kGy
4. PBS and Ascorbate, 0 kGy
5. PBS and Ascorbate, 45 kGy
6. PPG400, 0 kGy
7. PPG400, 45 kGy
8. Dehydrated in PPG400 and Rehydrated with PBS and Ascorbate, 0 kGy
9. Dehydrated in PPG400 and Rehydrated with PBS and Ascorbate, 45 kGy



1 2 3 4 5 6 7 8 9


22/54

FIG. 4H




23/54

FIG. 5A




24/54

FIG. 5B




25/54

FIG. 5C




26/54

FIG. 5D




27/54

FIG. 5E

28/54


FIG. 6A



29/54


FIG. 6B

Pepsin Digested Collagen



Cocktails: PPG/presoak; 100 μ M trolox, 100mM ascorbic acid,
100mM lipoic acid, 100mM n-propyl gallate

30/54


FIG. 6C

Cocktails : PPG/presoak; 100 μ M trolox, 100mM ascorbic acid,
100mM lipoic acid, 100mM n-propyl gallate

31/54


FIG. 6D

Protectants: PPG/presoak;
100 μ M trolox, C,
100mM coumestric acid,
100mM lipolic acid, and
100mM n-propyl gallate



32/54

FIG. 6E



33/54

FIG. 6F





FIG. 7A

Edmonton Cryopreservative

Modified VS55




Edmonton CP-M199, 10% FCS, 2 M DMSO, Pen-Strep
 Modified VS55: 100mM trehalose, 15mM KH₂PO₄, 42mM K₂HPO₄, 10mM NaHCO₃, 150mM mannitol,
 24.2% DMSO, 16.8% 1,2-propanediol, 14% formamide

FC: fresh ACL control
 Quick Freeze: dry-ice ethanol bath
 Regulated Freeze: decrease in temp. of 1°C/min to -56-59°C, then placed in -80°C


35/54

FIG. 7B



Edmonton CP: MI99, 10% FCS, 2 M DMSO, Pen-Strep
 Modified VS55: 100 mM trehalose, 15 mM KH_2PO_4 , 42 mM K_2HPO_4 , 15 mM KCl, 10 mM NaHCO_3 ,
 150 mM mannitol, 24.2% DMSO, 16.8% 1,2-propanediol, 14% formamide
 FC: fresh ACL control
 Quick Freeze: dry-ice ethanol bath
 Regulated Freeze: decrease in temp. of $1^\circ\text{C}/\text{min}$ to -56 – -59°C , then placed in -80°C

FIG. 7C



VS55: 100mM trehalose, 15mM KH_2PO_4 , 42mM K_2HPO_4 , 15mM KCl, 10mM NaHCO_3 , 150mM mannitol, 24.2% DMSO, 16.8% 1, 2-propanediol, and 14% formamide

CP: 10% FCS, Penicillin-streptomycin, M199, and 2M DMSO


37/54

FIG. 8




Cocktails: 100 μ M trolox, 100mM ascorbic acid, 100mM lipoic acid, 100mM n-propyl gallate

FIG. 9A



39/54

FIG. 9B



40/54

FIG. 11





FIG. 10



42/54

FIG. 12B




FIG. 12C






FIG. 13

Protectants	Control			Asc/GG			Protectants			Asc/GG			Methionine			Thiourea		
	Liq	Gel		Liq	Gel		Liq	Gel		Liq	Gel		Liq	Gel		Liq	Gel	
Dose (kGy)	0	50	0	50	0	50	0	50	0	50	0	50	0	50	0	50	0	50





45/54

FIG. 14A





46/54

FIG. 14B




47/54

FIG. 14C




48/54

FIG. 14D



49/54

FIG. 15

50/54

4M GdnHCl Extraction of porcine heart valve cusps gamma irradiated in modified VS55 Cryopreservative (+/-Asc)




FIG.16

51/54




FIG.17

52/54




FIG. 18

53/54




FIG. 19

54/54




FIG. 20

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/12827

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61L 2/08, 2/10; A01N 1/02

US CL : 422/22-24; 435/2

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 422/22-24; 435/2

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
Please See Continuation Sheet

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X — Y	US 5,730,933 A (PETERSON) 24 March 1998 (24.03.1998), see entire document.	1, 14-28, 32, 33, 37-39, 48-50, 54, 59-61, 66, 67, 91, 93-99, 109-113, 120, 130-134, 145 2, 5-8, 29, 52, 53, 55, 56, 87, 92, 100, 112, 117, 118, 121, 129, 144, 145
X — Y	US 5,981,163 A (HOROWITZ et al) 09 November 1999 (09.11.1999), see Abstract; Figures 2 and 3; col.6, lines 42-67; col.7, lines 1-10 and 39-45.	1, 41-47, 51, 109, 110, 112, 113, 120, 145 29, 55, 56



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

15 July 2003 (15.07.2003)

Date of mailing of the international search report

04 AUG 2003

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US
Commissioner for Patents
P.O. Box 1450
Alexandria, Virginia 22313-1450

Facsimile No. (703)305-3230

Authorized officer

Leigh McKane

Telephone No. 703-308-0661

INTERNATIONAL SEARCH REPORT

PCT/US03/12827

Continuation of B. FIELDS SEARCHED Item 3:
CAPLUS, BIOSIS, MEDLINE, EMBASE:
cryprotect?, radiat?, steril?

INTERNATIONAL SEARCH REPORT

PCT/US03/12827

C. (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X — Y	US 5,989,498 A (ODLAND) 23 November 1999 (23.11.1999), see entire document.	3, 9-13, 26, 37, 40, 47, 59, 60, 99, 109- 113, 120, 135-138, 140-143, 145, 29
Y	KAPANIN, P.V. et al. Abstract of "Feasibility of liposome cryoradiation sterilization," Khimiko-Farmatsevticheskii Zhurnal (1988), vol.22(4), pp.479-82.	2, 52, 53, 87, 92, 100, 112, 129, 145

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)